US 20230212739A1

(19) **United States**

(12) **Patent Application Publication**

GUO et al.

(10) **Pub. No.: US 2023/0212739 A1**

(43) **Pub. Date: Jul. 6, 2023**

(54) **ATOMIC LAYER DEPOSITION ON OPTICAL STRUCTURES**

(71) Applicant: **Applied Materials, Inc.**, Santa Clara, CA (US)

(72) Inventors: **Jinrui GUO**, San Jose, CA (US); **Ludovic GODET**, Sunnyvale, CA (US); **Rutger MEYER TIMMERMAN THIJSSEN**, Sunnyvale, CA (US)

(21) Appl. No.: **18/119,506**

(22) Filed: **Mar. 9, 2023**

Related U.S. Application Data

(63) Continuation of application No. 17/184,085, filed on Feb. 24, 2021, now Pat. No. 11,629,402, which is a continuation-in-part of application No. 16/795,232, filed on Feb. 19, 2020, now Pat. No. 11,572,619.

(60) Provisional application No. 62/865,001, filed on Jun. 21, 2019, provisional application No. 62/834,832, filed on Apr. 16, 2019.

Publication Classification

(51) **Int. Cl.**


C23C 16/455	(2006.01)
C23C 16/32	(2006.01)
C23C 16/04	(2006.01)

(52) **U.S. Cl.**

CPC ***C23C 16/45544*** (2013.01); ***C23C 16/325*** (2013.01); ***C23C 16/042*** (2013.01)

(57) **ABSTRACT**

Embodiments of the present disclosure generally relate to processing an optical workpiece containing grating structures on a substrate by deposition processes, such as atomic layer deposition (ALD). In one or more embodiments, a method for processing an optical workpiece includes positioning a substrate containing a first layer within a processing chamber, where the first layer contains grating structures separated by trenches formed in the first layer, and each of the grating structures has an initial critical dimension, and depositing a second layer on at least the sidewalls of the grating structures by ALD to produce corrected grating structures separated by the trenches, where each of the corrected grating structures has a corrected critical dimension greater than the initial critical dimension.






FIG. 1A




FIG. 1B




FIG. 1C



100
116
118
114
112
130
110
115
113
102

FIG. 1D



100
116
118
115
113
131
114
112
110
102

FIG. 1E



150
APPLY A MASK ON A FIRST PORTION OF A FIRST LAYER
152
DEPOSIT A SECOND LAYER ON THE MASK AND SECOND PORTION OF THE FIRST LAYER
154
REMOVE THE MASK
156
EXPOSE THE SECOND LAYER TO A CURING PROCESS
158

FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C



200
120 230
216
218
114
112
231
110
115
113
102

FIG. 3D



200
216
218
115
113
114
112
231
110
102

FIG. 3E



250
APPLY A SECOND LAYER ON A FIRST LAYER
252
APPLY A MASK ON A FIRST PORTION OF THE SECOND LAYER
254
EXPOSE THE MASK AND THE SECOND LAYER TO A CURING PROCESS
256
REMOVE THE MASK AND THE FIRST PORTION OF THE SECOND LAYER
258

FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F



350
352
DEPOSIT A SECOND LAYER ON A FIRST LAYER
354
EXPOSE THE SECOND LAYER TO A CURING PROCESS
356
APPLY A MASK ON A FIRST PORTION OF THE SECOND LAYER
358
EXPOSE THE MASK AND THE SECOND LAYER TO AN ETCHING PROCESS
360
REMOVE THE MASK

FIG. 6



700
112
114
114
114
114
115
115
115
115
111
θ
112
112
112
113
113
113
113
114
110
102

FIG. 7A



700
114B
114B
115B
115B
130
130
130
112
114
114
114B
114B
115B
115
115
113
115B
110
102

FIG. 7B




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D



900
112
114
114
114
114
115
115
111
θ
112
112
112
113
113
114
110
102

FIG. 9A



900
130
113 115
112
114
110
102

FIG. 9B

ATOMIC LAYER DEPOSITION ON OPTICAL STRUCTURES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation of U.S. application Ser. No. 17/184,085, filed Feb. 24, 2021, which is a continuation-in-part of U.S. application Ser. No. 16/795,232, filed Feb. 19, 2020, which claims benefit to U.S. Prov. Appl. No. 62/865,001, filed on Jun. 21, 2019, and U.S. Prov. Appl. No. 62/834,832, filed on Apr. 16, 2019, which are herein incorporated by reference in their entirety.

BACKGROUND

Field

[0002] Embodiments of the present disclosure generally relate to a method, and, more specifically, to a method of thin film deposition in trenches.

Description of the Related Art

[0003] In optical devices, such as virtual or augmented reality sets, a waveguide combiner is often used to couple a virtual image, transport light inside a glass substrate through total internal reflection, and then couple the image when reaching the position of viewer's eye. For light coupling and decoupling, slanted features and trenches in the waveguide combiner are usually applied as gratings for light diffraction. The orientation of lines (fins) controls the light propagation direction, whereas the tilted angle controls the efficiency of desired orders of diffraction.

[0004] Selective deposition in trenches has important industrial applications for optical devices. Precise control of the material properties of the deposited films, such as the refractive index, is necessary to ensure proper functioning of these devices. In addition, film growth without unwanted voids or holes is needed to ensure proper diffraction, reflection, and refraction of incident light on the optical structures. Thus, even film growth is required, along with selectivity, to ensure that the correct portions of the structures receive the films with desired material properties.

[0005] Traditional selective deposition processes often include chemical mechanical polishing (CMP) techniques to remove excess film growth and ensure that film growth occurs only in desired portions of the optical workpiece. However, CMP techniques are unable to remove film growth in trenches, as CMP techniques are surface level techniques. Also, the harsh mechanical condition during CMP can damage the underlying structures on the optical workpiece.

[0006] Therefore, improved methods for selectively depositing layers on an optical workpiece with grating structures are needed.

SUMMARY

[0007] Embodiments of the present disclosure generally relate to processing an optical workpiece containing grating structures on a substrate by deposition processes, such as atomic layer deposition (ALD). In one or more embodiments, a method for processing an optical workpiece includes positioning a substrate containing a first layer within a processing chamber, where the first layer contains grating structures separated by trenches formed in the first layer, and each of the grating structures has an initial critical dimension, and depositing a second layer on at least the sidewalls of the grating structures by ALD to produce corrected grating structures separated by the trenches, where each of the corrected grating structures has a corrected critical dimension greater than the initial critical dimension.

[0008] In other embodiments, a method for processing an optical workpiece includes applying a mask on a first layer disposed on a substrate, where the first layer contains grating structures separated by trenches formed in the first layer, the grating structures has a first group of the grating structures having a desired critical dimension and a second group of the grating structures having an initial critical dimension, the desired critical dimension is greater than the initial critical dimension, and the mask covers the first group of the grating structures and leaves exposed or bare the second group of the grating structures. The method also includes positioning the substrate containing the mask disposed on the first layer within a processing chamber, depositing a second layer on the second group of the grating structures by ALD to produce corrected grating structures separated by the trenches, where the corrected grating structures have a corrected critical dimension greater than the initial critical dimension, and removing the mask from the first layer, such that the first group of the grating structures and the corrected grating structures are exposed.

[0009] In other embodiments, a method for processing an optical workpiece includes positioning a substrate containing a first layer having a first refractive index within a processing chamber, where the first layer contains grating structures separated by trenches formed in the first layer, and the first layer contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof. The method also includes depositing a second layer having a second refractive index by ALD to completely fill the trenches and cover the grating structures, where the second layer contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof, and where a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] So that the manner in which the above recited features of the present disclosure can be understood in detail, a more particular description of the disclosure, briefly summarized above, may be had by reference to embodiments, some of which are illustrated in the appended drawings. It is to be noted, however, that the appended drawings illustrate only exemplary embodiments and are therefore not to be considered limiting of its scope, and may admit to other equally effective embodiments.

[0011] FIGS. **1**A-**1**E depict schematic views of an optical workpiece at different intervals during a process that includes depositing with a mask, according to one or more embodiments described and discussed herein.

[0012] FIG. **2** is a flow diagram of method operations for depositing a second layer on an optical workpiece using a mask, according to one or more embodiments described and discussed herein.

[0013] FIGS. **3**A-**3**E depict schematic views of an optical workpiece at different intervals during a process that

includes curing with a mask, according to one or more embodiments described and discussed herein.

[0014] FIG. **4** is a flow diagram of method operations for depositing a second layer on an optical workpiece using a curing process and a mask, according to one or more embodiments described and discussed herein.

[0015] FIGS. **5**A-**5**F depict schematic views of an optical workpiece at different intervals during a process that includes etching with a mask, according to one or more embodiments described and discussed herein.

[0016] FIG. **6** is a flow diagram of method operations for depositing a second layer on an optical workpiece using a mask and an etching process, according to one or more embodiments described and discussed herein.

[0017] FIGS. **7**A-**7**B depict schematic views of an optical workpiece at different intervals during a process that includes depositing a corrective layer on grating structures, according to one or more embodiments described and discussed herein.

[0018] FIGS. **8**A-**8**D depict schematic views of an optical workpiece at different intervals during a process that includes depositing with a mask and depositing a corrective layer on grating structures, according to one or more embodiments described and discussed herein.

[0019] FIGS. **9**A-**9**B depict schematic views of an optical workpiece at different intervals during a process that includes depositing a gap-fill layer between the grating structures, according to one or more embodiments described and discussed herein.

[0020] To facilitate understanding, identical reference numerals have been used, where possible, to designate identical elements that are common to the Figures. It is contemplated that elements and features of one or more embodiments may be beneficially incorporated in other embodiments.

DETAILED DESCRIPTION

[0021] Embodiments of the present disclosure generally relate to processing an optical workpiece containing a plurality of features and trenches. The optical workpieces can be or include workpieces, devices, or film stacks used as virtual reality (VR) devices, augmented reality (AR) devices, as well as other devices, including optical devices, display devices, and/or microelectronic devices. A combination of masks, curing, and etches allows for selective deposition on various portions of the optical workpiece. Films are selectively deposited on only certain parts of an optical workpiece, filling some trenches, and not filling others. The embodiments disclosed herein are especially useful for, but not limited to, selectively depositing film material in certain trenches, while preventing deposition in other trenches.

Mask Deposition Followed by Second Layer Deposition

[0022] FIG. **1**A depicts an optical workpiece **100** which includes a first layer **110** disposed on a substrate **102**. The first layer **110** can include a plurality of structures **114**, **115** formed therein. The plurality of structures **114**, **115** can include vertical fins, slanted fins, or pillars (e.g., nanopillars). A plurality of trenches **112**, **113** are formed or otherwise defined within the first layer **110** and between the structures **114**, **115**. The trenches **112**, **113** include one or more passageways, vias, spaces, gaps, voids, or holes adjacent any of the structures **114**, **115**. Each of the trenches **112**, **113** can independently be at an angle θ to the surface of the first layer **110**, such as from about 15° to about 75°. Each of the trenches **112**, **113** can independently have the same or different angle θ of the other spaces. In some embodiments, the angle θ can be from about 15°, about 20°, about 25°, or about 30° to about 45°, about 55°, about 65°, or about 75°.

[0023] Each trench **112**, **113** can independently have the same or different trench spacing, such as the spacing between adjacent trenches. Each of the trenches **112**, **113** can independently have the same or different widths of the other trenches. Each of the trenches **112**, **113** can independently have the same or different depths of the other trenches. Each of the trenches **112**, **113** can independently have a depth of about 100 nm, about 150 nm, about 200 nm, or about 300 nm to about 400 nm, about 500 nm, about 800 nm, or about 1,000 nm. Each of the trenches **112**, **113** can independently have a width of about 50 nm, about 80 nm, about 100 nm, or about 120 nm to about 150 nm, about 200 nm, about 400 nm, or about 600 nm. Each of the trenches **112**, **113** can independently have a trench spacing of about 50 nm, about 80 nm, about 100 nm, or about 120 nm to about 150 nm, about 200 nm, about 400 nm, or about 600 nm. Each of the trenches **112**, **113** can independently have an aspect ratio (AR) of about 1, about 1.5, about 1.8, or about 2 to about 2.2, about 2.5, about 3, about 3.5, about 4, about 5, or greater.

[0024] The optical workpiece **100** has a second plurality of structures **114** and a second plurality of trenches **112** disposed in the second portion **118** of the first layer **110**, the structures separated by the trenches. The first plurality of trenches **113** has at least one trench that makes an angle θ of about 15° to about 75° with respect to the top or upper surface **111** of the first layer **110**, according to one or more embodiments described and discussed herein. The second plurality of trenches **112** has at least one trench that makes an angle θ of about 15° to about 75° with respect to the surface of the first layer **110**, according to one or more embodiments described and discussed herein. The angles θ of the first trench **113** and the second trench **112** can be the same or different from one another.

[0025] In some embodiments, the first layer **110** is a surface of the substrate **102**, and the substrate **102** can include one or more structures **114**, **115**. The substrate **102** can include a wafer or panel substrate capable of having material, layers, films, and/or the like deposited thereon. The substrate **102** can include silicon (doped or undoped), crystalline silicon (e.g., Si<100> or Si<111>), strained silicon, silicon oxide, doped or undoped polysilicon, or the like, a germanium substrate, a silicon germanium substrate, a Group III-V compound substrate, such as a gallium arsenide substrate, a gallium nitride substrate, a silicon carbide substrate, a patterned or non-patterned semiconductor-on-insulator (SOI) substrate, a carbon-doped oxide, a silicon nitride, glass, sapphire, quartz, one or more polymeric materials, a solar array, solar panel, a light emitting diode (LED) substrate, or any other materials such as metals, metal alloys, and other conductive materials, or any combination thereof. In some examples, the substrate **102** can be disposed on a substrate holder or a substrate pedestal, a chucking plate, or the like. The substrate **102** can include a plurality of layers or films, such as a semi-insulating material and a semiconducting material, where the semi-insulating material has a higher resistivity than the semiconducting material. The

substrate **102** is not limited to any particular size or shape (e.g., round, rectangular, or square), or may have various dimensions. In some examples, the substrate **102** is round and has a diameter of 100 mm, 200 mm, 300 mm, 450 mm, or other diameter substrates.

[0026] In other embodiments, the first layer **110** can be or include one or more materials disposed on the substrate **102**. The first layer **110** can be or include monocrystalline silicon, polysilicon, amorphous silicon, silicon nitride, silicon oxide, silicon dioxide, silicon oxynitride, silicon oxycarbide, fused silica, one or more metal oxides (e.g., titanium oxide, niobium oxide, aluminum oxide, tantalum oxide), doped derivatives thereof, or any combination thereof. In one or more examples, the first layer **110** can have a refractive index (RI) of about 1.05 to about 4.50. The first layer **110** is deposited or otherwise formed by one or more processes or techniques, such as chemical vapor deposition (CVD), plasma-enhanced CVD (PE-CVD), sub-atmospheric CVD (SA-CVD), high density plasma CVD (HDP-CVD), flowable CVD (FCVD® processes), atomic layer deposition (ALD), furnace ALD, thermal ALD, plasma-enhanced ALD (PE-ALD), physical vapor deposition (PVD), ion beam deposition, spin-coating, or any combination thereof.

[0027] In one or more embodiments, the first layer **110** has a thickness of about 40 nm, about 50 nm, about 60 nm, about 80 nm, or about 100 nm to about 120 nm, about 150 nm, about 180 nm, about 200 nm, about 250 nm, about 300 nm, about 350 nm, about 400 nm, about 500 nm, or thicker. For example, the first layer **110** has a thickness of about 40 nm to about 500 nm, about 40 nm to about 300 nm, about 40 nm to about 250 nm, about 40 nm to about 200 nm, about 40 nm to about 180 nm, about 40 nm to about 160 nm, about 40 nm to about 150 nm, about 40 nm to about 120 nm, about 40 nm to about 100 nm, about 40 nm to about 80 nm, about 80 nm to about 500 nm, about 80 nm to about 300 nm, about 80 nm to about 250 nm, about 80 nm to about 200 nm, about 80 nm to about 180 nm, about 80 nm to about 160 nm, about 80 nm to about 150 nm, about 80 nm to about 120 nm, about 80 nm to about 100 nm, about 120 nm to about 500 nm, about 120 nm to about 300 nm, about 120 nm to about 250 nm, about 120 nm to about 200 nm, about 120 nm to about 180 nm, about 120 nm to about 160 nm, or about 120 nm to about 150 nm.

[0028] FIG. **2** is a flow diagram of method operations **150** for depositing a second layer **130** on the first layer **110** using a mask **120**, according to one or more embodiments described and discussed herein. Although the method **150** operations are described in conjunction with FIGS. **1**A-**1**E and **2**, persons skilled in the art will understand that any system configured to perform the method operations, in any order, falls within the scope of the embodiments described herein.

[0029] The method **150** begins at operation **152**, where a mask **120** is applied, placed, deposited, formed, or otherwise disposed on the first layer **110**, as depicted in FIG. **1**B. The mask **120** has a predetermined pattern that can be transposed to the underlying layer, such as the first layer **110**. The mask **120** covers a first portion **116** of the first layer **110** and leaves exposed a second portion **118** of the first layer. The mask **120** can be or include a contact mask, a proximity mask, a projection mask, or dicing tape. The mask **120** can be separate from the processing chamber, or inside the processing chamber as a movable part. In some examples, the mask **120** can be or include a photo mask in a UV cure process and can be incorporated into a UV chamber or a photolithography tool.

[0030] The mask **120** has a thickness from about 10 μm to about 1 mm, such as from about 100 μm to about 500 μm. The thickness of the mask **120** can be designed to reduce the shadowing effect, which can produce non-uniform deposition close to the edge of the mask. For example, the mask **120** has a relatively small thickness, e.g., from about 100 μm to about 150 μm, to reduce the shadowing effect.

[0031] At operation **154** of the method **150**, a second layer **130** is deposited on the second portion **118** of the first layer **110**, as well as the mask **120**, as depicted in FIG. **1**C. The second layer **130** is at least partially deposited within the second plurality of trenches **112**. The mask **120** covers and can substantially or completely protect or shield the first portion **116** of the first layer **110** from the second layer **130** depositing on the first portion **116**. In some examples, residual amounts of material of the second layer **130** can eventually contaminate the first portion **116** of the first layer **110**. Also, depending on the composition of the second layer **130** and the specific deposition process used to deposit or otherwise form the second layer **130**, the mask **120** can include a layer **132** of the same material as the second layer **130** and/or can contain various byproducts, particulates, and/or other contaminants thereon.

[0032] The second layer **130** is deposited or otherwise formed by CVD, PE-CVD, SA-CVD, HDP-CVD, flowable CVD (FCVD® processes), ALD, furnace ALD, thermal ALD, PE-ALD, PVD, ion beam deposition, spin-coating, or any combination thereof. The second layer **130** includes a coating material, such as spin-on-carbon, epoxy, naphthalene resin (C_{10}-C_8), organic planarization layer (OPL), poly (methyl methacrylate) (PMMA), polysilazane, polysiloxane, photoresists, or electron-beam (e-beam) resists. The second layer **130** can also include silicon oxide, silicon dioxide, silicon oxynitride, silicon nitride, silicon carbide, silicon oxycarbide, silicon hydroxynitride (SiOHN), amorphous silicon (α-Si), polysilicon, silicon-containing anti-reflective coating (Si-ARC), aluminum oxide, carbon, alloys thereof, doped derivatives thereof, or any combination thereof. In one or more examples, the second layer **130** can have a refractive index of about 1.05 to about 4.50. The optical and gap fill properties of the second layer **130** can be tuned through polymer type and functional groups. For example, methyl (CH_3—) groups or cage-like hydrogen silsesquioxane (HSQ) groups are known to reduce the RI of the second layer **130**.

[0033] A silicon precursor, such as trisilylamine (TSA) ($N(SiH_3)_3$), silanes, tetrasilane (Si_4H_{10}), tetraethyl orthosilicate (TEOS), tetramethoxysilane (TMOS), or octamethylcyclotetrasiloxane (OMCTS), can be used to deposit silicon-containing second layers **130**, such as silicon, silicon oxide, or silicon oxynitride, during a CVD process. A silicon precursor, such as trisilylamine (TSA) and a nitrogen precursor, such as ammonia (NH_3), can be used to deposit a silicon oxynitride layer during a CVD process. A silicon precursor, such as polysiloxane, can be used to deposit a silicon oxide layer during a spin-on process.

[0034] In one or more embodiments, the second layer **130** has a thickness of about 5 nm, about 10 nm, about 15 nm, about 20 nm, about 30 nm, or about 40 nm to about 50 nm, about 60 nm, about 70 nm, about 80 nm, about 90 nm, about 100 nm, or thicker. For example, the second layer **130** has

a thickness of about 5 nm to about 100 nm, about 5 nm to about 80 nm, about 5 nm to about 65 nm, about 5 nm to about 50 nm, about 5 nm to about 40 nm, about 5 nm to about 35 nm, about 5 nm to about 30 nm, about 5 nm to about 25 nm, about 5 nm to about 20 nm, about 5 nm to about 15 nm, about 5 nm to about 10 nm, about 10 nm to about 100 nm, about 10 nm to about 80 nm, about 10 nm to about 65 nm, about 10 nm to about 50 nm, about 10 nm to about 40 nm, about 10 nm to about 35 nm, about 10 nm to about 30 nm, about 10 nm to about 25 nm, about 10 nm to about 20 nm, about 10 nm to about 15 nm, about 20 nm to about 100 nm, about 20 nm to about 80 nm, about 20 nm to about 65 nm, about 20 nm to about 50 nm, about 20 nm to about 40 nm, about 20 nm to about 35 nm, about 20 nm to about 30 nm, or about 20 nm to about 25 nm.

[0035] The deposition of the second layer **130** can be performed at a substrate temperature or a processing chamber temperature from about 23° C. to about 400° C. For example, a CVD or ALD process can be performed at a substrate temperature or a processing chamber temperature from about 23° C. to about 100° C. A spin coating process can be performed at a substrate temperature or a processing chamber temperature at about 23° C. A wet etch can be performed after deposition of the second layer **130**, in order to remove residual deposition of the second layer present under the mask **120**.

[0036] At operation **156** of the method **150**, the mask **120** is removed from the first portion **116** of the first layer **110**. Thereafter, the first portion **116** of the first layer **110** is exposed or left bare and the second portion **118** of the first layer **110** contains the second layer **130** deposited thereon, as depicted in FIG. **1**D. Various materials (e.g., the layer **132**), particulate, or other contaminant contained on the mask **120** can be removed before removing the mask **120** and/or at the same time. The mask **120** and the first portion **116** of the second layer **130** are removed in the same processing step, according to one or more embodiments described and discussed herein. The mask **120** and the first portion **116** of the second layer **130** are sequentially removed in different processing steps, according to one or more embodiments described and discussed herein.

[0037] In one or more embodiments, the method **100** can include removing residual material from the first portion **116** of the first layer **110** during an etching process subsequent to removing the mask **120**. The etching process can include a wet etch process and includes exposing the residual material to a solution containing hydrofluoric acid (HF), phosphoric acid (H_3PO_4), one or more hydroxides (e.g., sodium hydroxide (NaOH), potassium hydroxide (KOH), lithium hydroxide (LiOH), ammonium hydroxide (NH_4OH)), or salts thereof. A dilute hydrofluoric acid (DHF) solution having a concentration from about 50:1 to about 1,000:1 (in water) can be used during an etching process, such as for a second layer **130** including silicon oxynitride. The etching process can be a dry etch process and includes exposing the residual material to a plasma containing fluorine (F), chlorine (CI), compounds thereof, ions thereof, or any combination thereof, such as for a second layer **130** including silicon oxynitride.

[0038] At operation **158** of the method **150**, the second layer **130** is converted to a cured composition **131**, as depicted in FIG. **1**E. The curing process drives out unwanted solvents from the second layer **130**, solidifies and stabilizes the second layer, and can also modify chemical and optical properties of the second layer, converting the second layer to the cured composition **131**. The curing process or treatment can be or include a thermal curing process, an ultraviolet (UV) curing process, a plasma-assisted treatment process, an ion beam treatment process, an electron beam (e-beam) treatment, or any combination thereof, according to some embodiments.

[0039] The curing process can be performed at a temperature from about 23° C. to about 400° C. If UV light is applied, the UV wavelength can be a broadband wavelength from about 190 nm to about 500 nm, or single wavelength excimer lasers with wavelengths of about 193 nm, 248 nm, or 365 nm. The UV curing time can vary from about 1 minute to about 10 minutes. The second layer **130** is exposed to ozone (O_3) during the curing process, according to one or more embodiments described and discussed herein. In some embodiments, the curing process can include exposing the second layer **130** to one or more processing gases or compounds during the treatment or process, such as argon (Ar), helium (He), oxygen (O_2), ozone, hydrogen gas (H_2), nitrogen gas (N_2), ammonia, water, ethylene (C_2H_4), acetylene (C_2H_2), or any combination thereof. The curing process is used to modify the second layer **130** film composition and stress as required for a given application. Optical properties of the second layer **130** can be tuned by material design (choice of polymer and functional groups, binder, and solvent), and baking condition (e.g., step-wise baking) to control crosslinking, solvent evaporation, and formation of nanoporosity. In addition, the cured composition **131** is easier or more difficult to remove from the optical workpiece **100** than the unmodified second layer **130**.

[0040] For example, a second layer **130** including FCVD-deposited silicon hydroxynitride can be cured into a cured composition **131** including silicon oxide. In an additional example, a second layer **130** including a spin coating-deposited polymer and solvent layer can be cured into the cured composition **131** which includes a cross-linked polymer.

[0041] In one or more embodiments, the second layer **130** is deposited using FCVD using $TSA/NH_3/O_2$ precursors at a temperature from about 23° C. to about 100° C., the second layer is cured using a baking process at temperatures from about 23° C. to about 400° C. while ozone is applied, and a wet etch including DHF is applied.

[0042] In other embodiments, the second layer **130** is deposited using spin coating, the second layer includes an organic planarization layer (OPL) including a polymer including C and H, the second layer is cured using a baking process at temperatures from about 250° C. to about 400° C., and a wet etch including a sulfuric peroxide mix (SPM) is applied.

[0043] As described above, a mask is deposited on a first layer. A second layer is deposited on the optical workpiece, but the mask prevents deposition of the second layer in the first plurality of trenches disposed underneath the mask. The mask is removed, and thus the second layer is grown such that material of the second layer is present in the second plurality of trenches, but not the first plurality of trenches.

[0044] The mask protects the first plurality of trenches from being filled with the second layer, while still allowing the second plurality of trenches to be filled with the second layer. The method as described above works well for films that do not require curing in order to be removed from the optical workpiece.

Second Layer Deposition Followed by Mask Deposition

[0045] FIG. **3**A depicts an optical workpiece **200**, which includes the first layer **110** disposed on the substrate **102** and containing the plurality of trenches **112**, **113** and the one or more structures **114**, **115** as previously discussed for the optical workpiece **100** in FIG. **1**A.

[0046] FIG. **4** is a flow diagram of method **250** operations for depositing a second layer **230** on the optical workpiece **200**, including curing and using a mask **120**, according to one or more embodiments described and discussed herein. Although the method **250** operations are described in conjunction with FIGS. **3**A-**3**E and **4**, persons skilled in the art will understand that any system configured to perform the method operations, in any order, falls within the scope of the embodiments described herein.

[0047] The method **250** begins at operation **252**, where a second layer **230** containing an uncured composition is applied, placed, deposited, or otherwise disposed on the first layer **110**, as depicted in FIG. **3**B. The second layer **230** fills the first plurality of trenches **113** and the second plurality of trenches **112**. The second layer **230** also extends along and covers the first layer **110**. The second layer **230** is deposited by any of the methods disclosed in the discussion of the deposition of second layer **130** FIG. **1**B above. The materials of the second layer **230** are similar to those of the second layer **130** described above. The deposition of the second layer **230** can be performed at a substrate temperature or a processing chamber temperature similar to that of the second layer **130** described above.

[0048] At operation **254** of the method **250**, the mask **120** is applied, placed, deposited, formed, or otherwise disposed on the second layer **230**, as depicted in FIG. **3**C. The content of the mask **120** and the application of the mask are similar to those of operation **152** described above.

[0049] At operation **256** of the method **250**, the optical workpiece **200**, including the mask **120** and a second portion **218** of the second layer **230**, is exposed to a curing process, as depicted in FIG. **3**D. The mask **120** shields or otherwise protects a first portion **216** of the second layer **230** from the curing process while the second portion **218** of the second layer **230** is at least partially cured, substantially cured, or completely cured during the curing process. Subsequent to the curing process, the first portion **216** of the second layer **230** contains the uncured composition. The second portion **218** of the second layer **230** contains a cured composition **231** formed from the uncured composition during the curing process. The curing process is similar to that of the operation **158** described above.

[0050] At operation **258** of the method **250**, the mask **120** and the first portion **216** of the second layer **230** containing the uncured composition are removed from the optical workpiece **200**, as depicted in FIG. **3**E. The mask **120** can be removed before removing the first portion **216** of the second layer **230**. The mask **120** and the first portion **216** of the second layer **230** can be removed during the same process. The first portion **216** of the layer can be removed by an etching process. The etching process can include a wet etch process and includes exposing the uncured material to a solution containing hydrofluoric acid, phosphoric acid, one or more hydroxides (e.g., sodium hydroxide, potassium hydroxide, lithium hydroxide, ammonium hydroxide), or salts thereof. In one or more examples, a DHF solution having a concentration from about 50:1 to about 1,000:1 (in water) is used during an etching process. The etching process can include a dry etch process and includes exposing the uncured material to plasma containing oxygen, fluorine, chlorine, compounds thereof, ions thereof, or any combination thereof.

[0051] In other embodiments, the second layer **330** is deposited using FCVD using $TSA/NH_3/O_2$ precursors at a temperature from about 23° C. to about 100° C., the second layer is cured using a baking process at temperatures from about 0° C. to about 400° C. while ultraviolet (UV) light is at a wavelength of about 193 nm to about 500 nm for about 1 minute to about 10 minutes, and a dry or wet etch including DHF is applied.

[0052] In other embodiments, the second layer **330** is deposited using FCVD using $OMCTS/TMOS/O_2$ precursors at a temperature from about 23° C. to about 100° C., the second layer is cured using a baking process at temperatures from about 0° C. to about 400° C. while ultraviolet (UV) light is applied at a wavelength of about 193 nm to about 500 nm for about 1 minute to about 10 minutes, and a dry etch including oxygen plasma is performed.

[0053] As described above, a second layer is deposited on the first layer, filling both the first plurality of trenches and the second plurality of trenches. A mask is placed over the first portion of the second layer, and the mask protects the first layer from the curing process. The curing process converts the exposed second portion of the second layer into a cured composition. When the mask is removed, the first portion of the second layer is removed along with the mask. The remaining cured composition fills the second plurality of trenches, but the first plurality of trenches is empty.

[0054] The mask protects the first plurality of trenches from being cured with the second layer, while still allowing the second plurality of trenches to be filled with the cured second layer. The method as described above works well for films that require curing after deposition.

Second Layer Deposition Followed by Etching Process

[0055] FIG. **5**A depicts an optical workpiece **300**, which includes a first layer **110** disposed on the substrate **102** and containing the plurality of trenches **112**, **113** and the plurality of structures **114**, **115** as previously discussed for the optical workpiece **100** in FIG. **1**A.

[0056] FIG. **6** is a flow diagram of method **350** operations for depositing a second layer **330** on the optical workpiece **300**, including using the mask **120** and an etching process, according to one or more embodiments described and discussed herein. Although the method **350** operations are described in conjunction with FIGS. **5**A-**5**F and **6**, persons skilled in the art will understand that any system configured to perform the method operations, in any order, falls within the scope of the embodiments described herein.

[0057] The method **350** begins at operation **352**, where a second layer **330** containing an uncured composition is deposited, formed, placed, or otherwise disposed on the first layer **110**, as depicted in FIG. **5**B. The second layer **330** fills the first plurality of trenches **113** and the second plurality of trenches **112**. The second layer **330** also extends along and covers the first layer **110**. The second layer **330** is deposited by any of the methods disclosed in the discussion of FIG. **1**B above. The materials of the second layer **330** are similar to those of the second layer **130** described above. The deposition of the second layer **330** can be performed at a substrate

temperature or a processing chamber temperature similar to that of second layer **130** described above.

[0058] At optional operation **354** of the method **350**, the second layer **330** is exposed to a curing process, converting the second layer to a modified second layer **331**, as depicted in FIG. **5**C. The curing process is similar to that described in operation **158** as described above. Although the following operations refer to the modified second layer **331**, it is to be understood that the same process can be applied to the second layer **330** as deposited, without the curing process described above.

[0059] At operation **356** of the method **350**, the mask **120** is applied, placed, deposited, formed, or otherwise disposed on the second layer **330**, as depicted in FIG. **5**D. The deposition of the mask **120** is similar to that described in operation **152** as described above.

[0060] At operation **358** of the method **350**, the optical workpiece **300**, including the mask **120** and a second portion **318** of the modified second layer **331**, is exposed to an etching process, as depicted in FIG. **5**E. The mask **120** shields or otherwise protects a first portion **316** of the second layer **330** from the etching process, while the second portion **318** of the modified second layer **331** is at least partially etched away. Subsequent to the etching process, the first portion **316** of the modified second layer **331** is not completely removed. The second portion **318** of the modified second layer **331** is at least partially removed, and the modified second layer is at least partially removed from the second plurality of trenches **112**.

[0061] The etching process can include a wet etch and/or a dry etch. The wet etch includes exposing the optical workpiece **300** to an etching chemical, which can include DHF, one or more hydroxides (e.g., KOH, NaOH), sulfuric peroxide mix (SPM), phosphoric acid, or any combination of the above. The dry etch includes exposing the optical workpiece **300** to an etching chemical, which can include fluorine-based chemicals, chlorine-based chemicals, oxygen-based chemicals, or any combination of the above. The etch can be performed at temperatures from about 23° C. to about 200° C.

[0062] The etching chemistry is based on the composition of the modified second layer **331** to be removed. For example, DHF or hydrofluorocarbons (HFC) can be used to remove the modified second layer **331** including silicon oxide, phosphoric acid (H_3PO_4) can be used to remove a modified second layer including silicon nitride, and sulfuric peroxide mix (SPM) or oxygen plasma can be used to remove a modified second layer including carbon.

[0063] At operation **360** of the method **350**, the mask **120** is removed from the optical workpiece **300**, as depicted in FIG. **5**F. The mask **120** is removed similarly to the process described in operation **156** above.

[0064] In one or more embodiments, the second layer **330** is deposited using spin coating, the second layer includes diazonaphthoquinone (DNQ) and/or novolac, the second layer is cured while ultraviolet (UV) light is applied at a wavelength of about 193 nm to about 500 nm for about 1 minute to about 10 minutes, and a dry etch including oxygen plasma is applied.

[0065] In other embodiments, the second layer **330** is deposited using spin coating, the second layer includes polysiloxane or polysilazane, the second layer is cured using a baking process at temperatures from about 0° C. to about 400° C. while ultraviolet (UV) light is applied at a wavelength of about 193 nm to about 500 nm for about 1 minute to about 10 minutes, and a dry or wet etch is performed.

[0066] In other embodiments, the second layer **330** is deposited using spin coating, the second layer includes an organic planarization layer (OPL) including a polymer including C and H, the second layer is cured using a baking process at temperatures from about 250° C. to about 400° C., and a dry etch including oxygen plasma is applied.

[0067] As described above, a second layer is deposited on the first layer, filling both the first plurality of trenches and the second plurality of trenches. The second layer is exposed to a curing process, converting the second layer to a modified second layer. A mask is placed over the first portion of the second layer. The optical workpiece is exposed to an etching process, which removes the second portion of the modified second layer. Finally, the mask is removed. The remaining cured composition fills the first plurality of trenches, but the second plurality of trenches is empty.

[0068] The mask protects the second plurality of trenches from being filled with a cured second layer, while still allowing the first plurality of trenches to be filled with the cured second layer. The method as described above works well for films that require curing to be etched.

Exemplary Atomic Layer Deposition Processes

[0069] FIGS. **7**A-**7**B depict schematic views of an optical workpiece **700** at different intervals during a process that includes depositing the second layer **130**, a corrective layer, by ALD on grating structures **114**, **115**, according to one or more embodiments described and discussed herein. FIG. **7**A depicts the optical workpiece **700** which includes the substrate **102** containing the first layer **110**. The method for processing the optical workpiece **700** includes positioning the substrate **102** containing the first layer **110** within a processing chamber, such as an ALD chamber. In some examples, the first layer **110** is or contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof.

[0070] The first layer **110** contains grating structures **114**, **115** separated by the trenches **112**, **113** formed in the first layer **110**. For example, the grating structures **114** are generally separated by the trenches **112** and the grating structures **115** are generally separated by the trenches **113**. As previously discussed above, each of the trenches **112**, **113** can be independently positioned at an angle θ of about 15° to about 75° with respect to the top surface **111** of the first layer **110**, according to one or more embodiments described and discussed herein. Each of the grating structures **114**, **115** independently has an initial critical dimension, measured as the line width or thickness along the top surface **111** of the grating structures **114**, **115**.

[0071] In one or more embodiments, each of the grating structures **114**, **115** independently has an average thickness of about 30 nm, about 35 nm, about 40 nm, about 50 nm, about 60 nm, about 75 nm, about 80 nm, about 90 nm, or about 100 nm to about 110 nm, about 120 nm, about 135 nm, about 150 nm, about 180 nm, about 200 nm, about 225 nm, about 250 nm, about 300 nm, about 320 nm, about 335 nm, about 350 nm, or about 380 nm. For example, each of the grating structures **114**, **115** independently has an average thickness of about 30 nm to about 350 nm, about 30 nm to about 300 nm, about 30 nm to about 250 nm, about 30 nm to about 200 nm, about 30 nm to about 150 nm, about 30 nm

to about 120 nm, about 30 nm to about 100 nm, about 30 nm to about 80 nm, about 60 nm to about 350 nm, about 60 nm to about 300 nm, about 60 nm to about 250 nm, about 60 nm to about 200 nm, about 60 nm to about 150 nm, about 60 nm to about 120 nm, about 60 nm to about 100 nm, about 80 nm to about 350 nm, about 80 nm to about 300 nm, about 80 nm to about 250 nm, about 80 nm to about 200 nm, about 80 nm to about 150 nm, or about 80 nm to about 120 nm.

[0072] FIG. **7**B depicts the optical workpiece **700** further processed by having the second layer **130** deposited or otherwise disposed on the first layer **110** disposed on the substrate **102**. The second layer **130** is deposited by ALD on the first layer **110**, such as on top surfaces and the sidewalls of the grating structures **114**, **115** and on the bottom surfaces of the trenches **112**, **113**, which can include portions of the substrate **102** and/or the first layer **110**. In some examples, the method includes depositing the second layer **130** by ALD on at least the sidewalls of the grating structures **114**, **115** to produce corrected grating structures **114***b*, **115***b* separated by the trenches **112**, **113**. In other examples, the second layer **130** is deposited by ALD on the sidewalls and the top surfaces of the grating structures **114**, **115** to produce corrected grating structures **114***b*, **115***b* separated by the trenches **112**, **113**. The corrected grating structures **114***b*, **115***b* are the grating structures **114**, **115** coated by or otherwise containing the second layer **130**.

[0073] The second layer **130** is deposited by any type of ALD process including thermal ALD, PE-ALD, or atomic layer epitaxy (ALE). In some examples, the second layer **130** can be or include amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof. In one or more embodiments, some or all of the aspects of the method **250** (e.g., operation **252**) and/or the method **350** (e.g., operation **352**) can be applied to the optical workpiece **700** during the ALD processes or other fabrication processes or techniques, as described and discussed herein.

[0074] In one or more embodiments, the second layer **130** is deposited by ALD to a thickness of about 5 nm, about 10 nm, about 15 nm, about 20 nm, about 30 nm, or about 40 nm to about 50 nm, about 60 nm, about 70 nm, about 80 nm, about 90 nm, about 100 nm, or thicker. For example, the second layer 130 is deposited by ALD to a thickness of about 5 nm to about 100 nm, about 5 nm to about 80 nm, about 5 nm to about 65 nm, about 5 nm to about 50 nm, about 5 nm to about 40 nm, about 5 nm to about 35 nm, about 5 nm to about 30 nm, about 5 nm to about 25 nm, about 5 nm to about 20 nm, about 5 nm to about 15 nm, about 5 nm to about 10 nm, about 10 nm to about 100 nm, about 10 nm to about 80 nm, about 10 nm to about 65 nm, about 10 nm to about 50 nm, about 10 nm to about 40 nm, about 10 nm to about 35 nm, about 10 nm to about 30 nm, about 10 nm to about 25 nm, about 10 nm to about 20 nm, about 10 nm to about 15 nm, about 20 nm to about 100 nm, about 20 nm to about 80 nm, about 20 nm to about 65 nm, about 20 nm to about 50 nm, about 20 nm to about 40 nm, about 20 nm to about 35 nm, about 20 nm to about 30 nm, or about 20 nm to about 25 nm.

[0075] The initial critical dimensions of the grating structures **114**, **115** depicted in FIG. **7**A are modified by the second layer to produce the corrected grating structures **114***b*, **115***b* having a corrected critical dimension, as shown in FIG. **7**B. Each of the corrected grating structures **114***b*, **115***b* has a corrected critical dimension greater than the initial critical dimension.

[0076] Each of the corrected grating structures **114***b*, **115***b* independently has an average thickness of about 50 nm, about 60 nm, about 75 nm, about 90 nm, or about 100 nm to about 120 nm, about 135 nm, about 150 nm, about 180 nm, about 200 nm, about 225 nm, about 250 nm, about 300 nm, about 350 nm, or about 400 nm. For example, each of the corrected grating structures **114***b*, **115***b* independently has an average thickness of about 50 nm to about 400 nm, about 50 nm to about 300 nm, about 50 nm to about 250 nm, about 50 nm to about 200 nm, about 50 nm to about 150 nm, about 50 nm to about 120 nm, about 50 nm to about 100 nm, about 50 nm to about 80 nm, about 75 nm to about 400 nm, about 75 nm to about 300 nm, about 75 nm to about 250 nm, about 75 nm to about 200 nm, about 75 nm to about 150 nm, about 75 nm to about 120 nm, about 75 nm to about 100 nm, about 100 nm to about 400 nm, about 100 nm to about 300 nm, about 100 nm to about 250 nm, about 100 nm to about 200 nm, about 100 nm to about 150 nm, or about 100 nm to about 120 nm.

[0077] The average thickness of the corrected grating structures **114***b*, **115***b*, depicted in FIG. **7**B, is greater than an average thickness of the initial grating structures **114**, **115**, depicted in FIG. **7**A. In one or more examples, the corrected critical dimension or the average thickness of the corrected grating structures **114***b*, **115***b* is about 1%, about 3%, about 5%, about 7%, about 10%, about 12%, about 15%, about 18%, about 20%, about 22%, about 25%, about 30%, about 35%, about 40%, or about 50% to about 60%, about 65%, about 80%, about 100%, about 120%, about 150%, about 180%, about 200%, or about 250% greater than the initial critical dimension or an average thickness of the initial grating structures **114**, **115**. For example, the corrected critical dimension or the average thickness of the corrected grating structures **114***b*, **115***b* is about 10% to about 250%, about 10% to about 200%, about 10% to about 150%, about 10% to about 120%, about 10% to about 100%, about 10% to about 80%, about 10% to about 50%, about 50% to about 250%, about 50% to about 200%, about 50% to about 150%, about 50% to about 120%, about 50% to about 100%, about 50% to about 80%, about 100% to about 250%, about 100% to about 200%, about 100% to about 150%, or about 100% to about 120% greater than the initial critical dimension or an average thickness of the initial grating structures **114**, **115**.

[0078] In other examples, the corrected critical dimension or the average thickness of the corrected grating structures **114***b*, **115***b* is about 5% to about 80%, about 5% to about 65%, about 5% to about 50%, about 5% to about 40%, about 5% to about 30%, about 5% to about 25%, about 5% to about 20%, about 5% to about 18%, about 5% to about 15%, about 5% to about 10%, about 5% to about 8%, about 10% to about 80%, about 10% to about 65%, about 10% to about 50%, about 10% to about 40%, about 10% to about 30%, about 10% to about 25%, about 10% to about 20%, about 10% to about 18%, about 10% to about 15%, about 10% to about 12%, about 20% to about 80%, about 20% to about 65%, about 20% to about 50%, about 20% to about 40%, about 20% to about 30%, about 20% to about 25%, or about 20% to about 22% greater than the initial critical dimension or an average thickness of the initial grating structures **114**, **115**.

[0079] In one or more examples, the initial critical dimension or average thickness of the grating structures **114**, **115** is about 50 nm, the second layer 130 is deposited by ALD to a thickness of about 10 nm, so that the corrected critical dimension or average thickness of the corrected grating structures **114***b*, **115***b* is increased by about 20% to about 60 nm. In other examples, the initial critical dimension or average thickness of the grating structures **114**, **115** is about 250 nm, the second layer **130** is deposited by ALD to a thickness of about 50 nm, so that the corrected critical dimension or average thickness of the corrected grating structures **114***b*, **115***b* is increased by about 20% to about 300 nm. In some examples, the initial critical dimension or average thickness of the grating structures **114**, **115** is about 300 nm, the second layer **130** is deposited by ALD to a thickness of about 20 nm, so that the corrected critical dimension or average thickness of the corrected grating structures **114***b*, **115***b* is increased by about 7% to about 320 nm.

[0080] In one or more embodiments, the second layer **130** has the same or substantially the same refractive index as the first layer **110**. The first layer **110** has a first refractive index, the second layer **130** has a second refractive index, and the first and second refractive indexes are the same or substantially the same. The difference between the first refractive index and the second refractive index can be about +/−0.001 to about +/−0.1, about +/−0.001 to about +/−0.01, or about +/−0.01 to about +/−0.1.

[0081] In other embodiments, the second layer **130** has a substantially different refractive index compared to the refractive index of the first layer **110**. The second layer can be used to adjust or shift the refractive index if desired. In such embodiments, the difference between the first refractive index and the second refractive index can be about +/−0.1 to about +/−3, +/−0.1 to about +/−2, +/−0.1 to about +/−1, +/−0.5 to about +/−3, +/−0.5 to about +/−2, +/−0.5 to about +/−1, +/−1 to about +/−3, +/−1 to about +/−2, or +/−1 to about +/−2.5.

[0082] Each of the refractive index of the first layer **110** (e.g., first RI) and the refractive index of the second layer **130** (e.g., second RI) can independently be about 1.05, about 1.1, about 1.2, about 1.5, about 1.6, about 1.8, or about 2 to about 2.2, about 2.5, about 2.8, about 3, about 3.2, about 3.5, about 3.8, about 4, about 4.2, or about 4.5. For example, each of the refractive index of the first layer **110** and the refractive index of the second layer **130** can independently be about 1.05 to about 4.5, about 1.05 to about 4, about 1.05 to about 3.5, about 1.05 to about 3, about 1.05 to about 2.5, about 1.05 to about 2, about 1.05 to about 1.5, about 1.05 to about 1.3, about 1.5 to about 4.5, about 1.5 to about 4, about 1.5 to about 3.5, about 1.5 to about 3, about 1.5 to about 2.5, about 1.5 to about 2, about 1.5 to about 1.8, about 2 to about 4.5, about 2 to about 4, about 2 to about 3.5, about 2 to about 3, about 2 to about 2.5, or about 2 to about 2.2.

[0083] FIGS. **8**A-**8**D depict schematic views of an optical workpiece **800** at different intervals while being processed, according to one or more embodiments described and discussed herein. The process generally includes depositing with a mask **120** on a first portion of the first layer **110** and leaving exposed a second portion of the first layer **110**, selectively depositing by ALD the second layer **130** (e.g., a corrective layer) on the grating structures within the second portion of the first layer **110**, and removing the mask **120**. In one or more embodiments, some or all of the aspects of the method **150** (e.g., operations **152**, **154**, **156**) can be applied to the optical workpiece **800** during the ALD processes or other fabrication processes or techniques, as described and discussed herein.

[0084] FIG. **8**A depicts the optical workpiece **800** which includes the substrate **102** containing the first layer **110**. In some examples, the first layer **110** is or contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof. The first layer **110** contains the grating structures **114** generally separated by the trenches **112** and the grating structures **115** generally separated by the trenches **113**. As previously discussed above, each of the trenches **112**, **113** can be independently positioned at an angle θ of about 15° to about 75° with respect to the top surface **111** of the first layer **110**, according to one or more embodiments described and discussed herein. In one or more examples, the grating structures **114**, **115** contain a first group of the grating structures **115** having a desired critical dimension and a second group of the grating structures **114** having an initial critical dimension. The desired critical dimension of the grating structures **115** is greater than the initial critical dimension of the grating structures **114**.

[0085] FIG. **8**B depicts the mask **120** disposed on at least a portion of the first layer **110**. The mask **120** can be applied, deposited, or otherwise formed on the first layer **110**, such that the mask **120** covers the first group of the grating structures **115** and leaves exposed or bare the second group of the grating structures **114**.

[0086] FIG. **8**C depicts the second layer **130** deposited on the trenches **112** and the second group of the grating structures **114** by ALD to produce corrected grating structures **114***b* separated by the trenches **112**. The corrected grating structures **114***b* have a corrected critical dimension greater than the initial critical dimension due to the addition of the second layer **130**. The trenches **113** and the second group of the grating structures **115** stay exposed, bare, or otherwise free of the second layer **130**. The mask **120** can include a layer **132** of the same material as the second layer **130** and/or can contain various byproducts, particulates, and/or other contaminants thereon.

[0087] FIG. **8**D depicts the optical workpiece **900** after the mask **120** and the layer **132** have been removed from the first layer **110**. The trenches **113** and the second group of the grating structures **115** stay exposed, bare, or otherwise free of the mask **120**.

[0088] The corrected grating structures **114***b* and the grating structures **115** can have the same or substantially the same critical dimension. In one or more embodiments, the corrected critical dimension of the corrected grating structures **114***b* is about +/−10% of the desired critical dimension of the first group of the grating structures **115**. For example, the corrected critical dimension of the corrected grating structures **114***b* can be about +/−8%, about +/−5%, about +/−3%, about +/−2%, about +/−1%, about +/−0.5%, or about +/−0.1% of the desired critical dimension of the first group of the grating structures **115**.

[0089] FIGS. **9**A-**9**B depict schematic views of an optical workpiece **900** at different intervals while being processed that includes depositing by ALD the second layer **130** as a gap-fill layer between the grating structures **114**, **115**, according to one or more embodiments described and discussed herein. FIG. **9**A depicts the optical workpiece **900**

which includes the substrate **102** containing the first layer **110**. In some examples, the first layer **110** is or contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof. The first layer **110** contains the grating structures **114** generally separated by the trenches **112** and the grating structures **115** generally separated by the trenches **113**. As previously discussed above, each of the trenches **112**, **113** can be independently positioned at an angle θ of about 15° to about 75° with respect to the top surface **111** of the first layer **110**, according to one or more embodiments described and discussed herein.

[0090] The method for processing the optical workpiece **900** includes positioning the substrate **102** containing the first layer **110** within a processing chamber, such as an ALD chamber. FIG. **9**B depicts the optical workpiece **900** further processed by having the second layer **130** deposited or otherwise disposed on the first layer **110** disposed on the substrate **102**. The second layer **130** is deposited by ALD on the first layer **110**, such as on top surfaces and the sidewalls of the grating structures **114**, **115** and on the bottom surfaces of the trenches **112**, **113**, which can include portions of the substrate **102** and/or the first layer **110**. The second layer **130** is deposited by ALD to fill the trenches **112**, **113** while coating or otherwise depositing on the sidewalls and top surfaces of the grating structures **114**, **115**. In one or more embodiments, some or all of the aspects of the method **250** (e.g., operation **252**) and/or the method **350** (e.g., operation **352**) can be applied to the optical workpiece **900** during the ALD processes or other fabrication processes or techniques, as described and discussed herein.

[0091] In some embodiments, the first layer **110** and the second layer **130** have the same or substantially the same refractive indexes. For example, the difference between the refractive index of the first layer **110** and the refractive index of the second layer **130** can be about +/−0.001 to about +/−0.1, about +/−0.001 to about +/−0.01, or about +/−0.01 to about +/−0.1. In one or more examples, the first layer **110** contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof and the second layer **130** contains amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof.

[0092] In one or more embodiments, the processes **150**, **250**, and/or **350**, and/or any processes, operations, or portions thereof described and discussed herein, can be performed in a CVD chamber, such as a thermal CVD chamber, a PE-CVD chamber, a high-density plasma CVD chamber, a low pressure CVD chamber, a reduced pressure CVD chamber, or an atmospheric pressure CVD chamber. In other embodiments, the processes **150**, **250**, and/or **350**, and/or any processes, operations, or portions thereof described and discussed herein, can be performed in a PVD chamber, an ALD chamber, a PE-ALD chamber, an etch chamber (thermal or plasma), an epitaxy chamber, an anneal chamber, or any other processing chamber in which temperature monitoring might be useful. Examples of the processing chamber can include CVD chambers such as AKT® PECVD chambers, PRODUCER™ chambers, Eterna FCVD® chambers, and PRECISION 5000® chambers, commercially available from Applied Materials Inc., Santa Clara, Calif.

[0093] In other embodiments, the surfaces of the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** are exposed to a dry-clean treatment to remove oxides, carbons, particulates, and/or other contaminants during the processes **150**, **250**, and/or **350**, and/or any processes, operations, or portions thereof described and discussed herein. Any suitable dry-clean treatment process that removes oxides from the substrate without significantly damaging the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** can be used. Suitable dry-clean treatment processes include sputter etch processes, plasma-based oxide etch processes, or combinations thereof. The dry-clean treatment can include exposing the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** to an etchant and to plasma, ions, radicals, or a combination thereof. The etchant can be or include one or more of oxygen, fluorine, chlorine, nitrogen, plasmas thereof, ions thereof, radicals thereof, or any combination thereof. The dry-clean treatment includes exposing the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** to a fluorine plasma generated from a combination of nitrogen trifluoride (NF_3) and ammonia (NH_3). Other contemplated etch processes include NF_3/NH_3 inductively coupled plasma processes or NF_3/NH_3 capacitively coupled plasma processes.

[0094] In one or more embodiments, the dry-clean treatment is a plasma-based oxide etch process that is a remote plasma assisted dry etch process which involves the simultaneous exposure of a substrate to NF_3 and NH_3 plasma by-products. In some examples, the plasma-based oxide etch process can include a SICONI® etch process that is commercially available from Applied Materials, Inc. of Santa Clara, Calif. The SICONI® etch process can be performed in a SICONI® Preclean chamber, commercially available from Applied Materials, Inc. of Santa Clara, Calif.

[0095] In some examples that use remote plasma, excitation of the gas species allows plasma-damage-free substrate processing. The remote plasma etch can be largely conformal and selective towards silicon oxide layers, and thus does not readily etch silicon regardless of whether the silicon is amorphous, crystalline or polycrystalline. The remote plasma process will generally produce solid by-products which grow on the surface of the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** as material is removed. The solid by-products can be subsequently removed via sublimation when the temperature of the optical workpieces **100**, **200**, **300**, **700**, **800**, **900** is raised (e.g., to about 300° C.). The plasma etch process results in the removal of oxides, particulate, and other contaminants from the surface of the optical workpieces **100**, **200**, **300**, **700**, **800**, **900**.

[0096] In some examples, the dry-clean treatment process can be performed or conducted in a processing chamber fluidly coupled to a remote plasma source (RPS) while treating the optical workpieces **100**, **200**, **300**, **700**, **800**, **900**. For example, the processing chamber can be an AKTIV PreClean® chamber, commercially available from Applied Materials, Inc. of Santa Clara, Calif. In other examples, the dry-clean treatment process can be performed in an etch chamber using an inductively coupled plasma (ICP) source. For example, the etch chamber can be a Centura® Advantedge® Mesa® Etch chamber, commercially available from Applied Materials, Inc. of Santa Clara, Calif. Alternatively, the cleaning process can be performed in an etch chamber employing a radical-based chemistry. The optical workpieces **100**, **200**, **300**, **700**, **800**, **900** is exposed to the etchant

during the dry-clean treatment to remove the contaminants for a period of about 20 minutes or less, for example, about 10 minutes.

[0097] In one or more embodiments, optical workpieces, including the optical workpieces **100**, **200**, **300**, **700**, **800**, **900**, can be or include workpieces, devices, or film stacks used as virtual reality (VR) devices, augmented reality (AR) devices, as well as other devices, including optical devices, display devices, and/or microelectronic devices.

[0098] In one or more examples, the chemical properties of deposited film are utilized to produce selectivity and pattern, instead of relying on photoresist/hard mask. In some embodiments, the mask can be a separate, removable, and/or reusable part transferring to the processing chamber with the optical workpiece and/or substrate, or incorporated as a hardware component in tool and/or processing chamber. In other embodiments, a binary mask can be a contact mask which is placed on the optical workpiece and transferred to the processing chamber together or incorporated to the processing chamber design.

[0099] Embodiments of the present disclosure further relate to any one or more of the following paragraphs 1-15:

[0100] 1. A method for processing an optical workpiece, comprising: positioning a substrate containing a first layer within a processing chamber, wherein the first layer comprises grating structures separated by trenches formed in the first layer, and wherein each of the grating structures has an initial critical dimension; and depositing a second layer on at least the sidewalls of the grating structures by atomic layer deposition to produce corrected grating structures separated by the trenches, wherein each of the corrected grating structures has a corrected critical dimension greater than the initial critical dimension.

[0101] 2. A method for processing an optical workpiece, comprising: applying a mask on a first layer disposed on a substrate, wherein the first layer comprises grating structures separated by trenches formed in the first layer, wherein the grating structures comprise a first group of the grating structures having a desired critical dimension and a second group of the grating structures having an initial critical dimension, wherein the desired critical dimension is greater than the initial critical dimension, and wherein the mask covers the first group of the grating structures and leaves exposed the second group of the grating structures; positioning the substrate containing the mask disposed on the first layer within a processing chamber; depositing a second layer on the second group of the grating structures by atomic layer deposition to produce corrected grating structures separated by the trenches, wherein the corrected grating structures have a corrected critical dimension greater than the initial critical dimension; and removing the mask from the first layer, wherein the first group of the grating structures and the corrected grating structures are exposed.

[0102] 3. A method for processing an optical workpiece, comprising: positioning a substrate containing a first layer having a first refractive index within a processing chamber, wherein the first layer comprises grating structures separated by trenches formed in the first layer, and wherein the first layer comprises amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof; and depositing a second layer having a second refractive index by atomic layer deposition to completely fill the trenches and cover the grating structures, wherein the second layer comprises amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof, and wherein a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1.

[0103] 4. The method according to any one of paragraphs 1-3, wherein an average thickness of the corrected grating structures is about 5% to about 200% greater than an average thickness of the grating structures.

[0104] 5. The method according to any one of paragraphs 1-4, wherein the corrected grating structures have an average thickness of about 50 nm to about 400 nm.

[0105] 6. The method according to any one of paragraphs 1-5, wherein the corrected critical dimension of the corrected grating structures is +/−10% of the desired critical dimension of the first group of the grating structures.

[0106] 7. The method according to any one of paragraphs 1-6, wherein the first layer has a first refractive index, the second layer has a second refractive index, and a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1.

[0107] 8. The method according to any one of paragraphs 1-7, wherein each of the first refractive index and the second refractive index is independently about 1.05 to about 4.50.

[0108] 9. The method according to any one of paragraphs 1-8, further comprising depositing the second layer on the top surfaces of the grating structures by the atomic layer deposition while depositing the second layer on the sidewalls.

[0109] 10. The method according to any one of paragraphs 1-9, wherein the second layer has a thickness of about 5 nm to about 100 nm.

[0110] 11. The method according to any one of paragraphs 1-10, wherein the trenches are positioned at an angle of about 15° to about 75° with respect to the top surface of the first layer.

[0111] 12. The method according to any one of paragraphs 1-11, further comprising applying a mask on the first layer prior to depositing the second layer, wherein the mask covers a first portion of the first layer and leaves exposed a second portion of the first layer, and wherein the grating structures are located in the second portion; depositing the second layer on the second portion of the first layer; and removing the mask from the first portion of the first layer, wherein the first portion of the first layer is exposed and the second portion of the first layer contains the second layer deposited thereon.

[0112] 13. The method according to any one of paragraphs 1-12, wherein the first layer comprises amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof.

[0113] 14. The method according to any one of paragraphs 1-13, wherein the second layer comprises amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof.

[0114] 15. An optical workpiece produced, manufactured, or otherwise formed by the method according to any one of paragraphs 1-14.

[0115] While the foregoing is directed to embodiments of the disclosure, other and further embodiments may be devised without departing from the basic scope thereof, and

the scope thereof is determined by the claims that follow. All documents described herein are incorporated by reference herein, including any priority documents and/or testing procedures to the extent they are not inconsistent with this text. As is apparent from the foregoing general description and the specific embodiments, while forms of the present disclosure have been illustrated and described, various modifications can be made without departing from the spirit and scope of the present disclosure. Accordingly, it is not intended that the present disclosure be limited thereby. Likewise, the term "comprising" is considered synonymous with the term "including" for purposes of United States law. Likewise, whenever a composition, an element, or a group of elements is preceded with the transitional phrase "comprising", it is understood that the same composition or group of elements with transitional phrases "consisting essentially of", "consisting of", "selected from the group of consisting of", or "is" preceding the recitation of the composition, element, or elements and vice versa, are contemplated. As used herein, the term "about" refers to a +/−10% variation from the nominal value. It is to be understood that such a variation can be included in any value provided herein.

[0116] Certain embodiments and features have been described using a set of numerical upper limits and a set of numerical lower limits. It should be appreciated that ranges including the combination of any two values, e.g., the combination of any lower value with any upper value, the combination of any two lower values, and/or the combination of any two upper values are contemplated unless otherwise indicated. Certain lower limits, upper limits and ranges appear in one or more claims below.

What is claimed is:

1. A method for processing an optical workpiece, comprising:

positioning a substrate containing a first layer comprising a carbide within a processing chamber, wherein the first layer comprises grating structures separated by trenches formed in the first layer, wherein the grating structures comprise a first group of the grating structures having a desired critical dimension and a second group of the grating structures having an initial critical dimension, and wherein the desired critical dimension is greater than the initial critical dimension;

applying a mask on the first layer, wherein the mask covers the first group of the grating structures and leaves exposed the second group of the grating structures; and

depositing a second layer on the mask and at least the sidewalls of the second group of the grating structures by vapor deposition to produce corrected grating structures separated by the trenches in the second group, wherein each of the corrected grating structures has a corrected critical dimension greater than the initial critical dimension.

2. The method of claim **1**, wherein the vapor deposition is atomic layer deposition.

3. The method of claim **1**, wherein the carbide further comprises silicon.

4. The method of claim **1**, wherein the carbide comprises silicon oxycarbide.

5. The method of claim **1**, wherein an average thickness of the corrected grating structures is about 5% to about 200% greater than an average thickness of the grating structures, and wherein the corrected grating structures have an average thickness of about 50 nm to about 400 nm.

6. The method of claim **1**, wherein the first layer has a first refractive index, the second layer has a second refractive index, and a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1, and wherein each of the first refractive index and the second refractive index is independently about 1.05 to about 4.50.

7. The method of claim **1**, further comprising depositing the second layer on the top surfaces of the grating structures by the vapor deposition while depositing the second layer on the sidewalls, and wherein the second layer has a thickness of about **5** nm to about 100 nm.

8. The method of claim **1**, wherein the trenches are positioned at an angle of about 15° to about 75° with respect to the top surface of the first layer.

9. The method of claim **1**, further comprising

removing the second layer deposited on the mask and removing the mask from the first layer, wherein the first group of the grating structures is exposed and the second group of the grating structures contains the second layer deposited thereon.

10. The method of claim **1**, wherein the first layer further comprises amorphous silicon, silicon nitride, silicon oxide, silicon oxynitride, silicon oxycarbide, titanium oxide, niobium oxide, dopants thereof, or any combination thereof.

11. The method of claim **1**, wherein the second layer comprises amorphous silicon, silicon carbide, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof.

12. The method of claim **1**, wherein the second layer comprises silicon carbide.

13. The method of claim **1**, wherein the substrate comprises silicon carbide.

14. A method for processing an optical workpiece, comprising:

applying a mask on a first layer comprising a carbide disposed on a substrate, wherein the first layer comprises grating structures separated by trenches formed in the first layer, wherein the grating structures comprise a first group of the grating structures having a desired critical dimension and a second group of the grating structures having an initial critical dimension, wherein the desired critical dimension is greater than the initial critical dimension, and wherein the mask covers the first group of the grating structures and leaves exposed the second group of the grating structures;

positioning the substrate containing the mask disposed on the first layer within a processing chamber;

depositing a second layer on the mask and the second group of the grating structures to produce corrected grating structures separated by the trenches, wherein the corrected grating structures have a corrected critical dimension greater than the initial critical dimension; and

removing the second layer deposited on the mask and removing the mask from the first layer, wherein the first group of the grating structures and the corrected grating structures are exposed.

15. The method of claim **14**, wherein the carbide further comprises silicon.

16. The method of claim **14**, wherein the second layer comprises silicon carbide.

17. The method of claim **14**, wherein the substrate comprises silicon carbide.

18. The method of claim **14**, wherein the corrected critical dimension of the corrected grating structures is +/−10% of the desired critical dimension of the first group of the grating structures, and wherein an average thickness of the corrected grating structures is about 5% to about 200% greater than an average thickness of the grating structures of the second group.

19. The method of claim **14**, wherein the first layer has a first refractive index, the second layer has a second refractive index, and a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1.

20. A method for processing an optical workpiece, comprising:

positioning a substrate containing a first layer having a first refractive index within a processing chamber, wherein the first layer comprises grating structures separated by trenches formed in the first layer, wherein the grating structures comprise a first group of the grating structures having a desired critical dimension and a second group of the grating structures having an initial critical dimension, wherein the desired critical dimension is greater than the initial critical dimension, and wherein the first layer comprises silicon and carbon;

applying a mask on the first layer, wherein the mask covers the first group of the grating structures and leaves exposed the second group of the grating structures;

depositing a second layer having a second refractive index, wherein the second layer is deposited on the mask and to completely fill the trenches of the second group and cover the grating structures of the second group, wherein the second layer comprises amorphous silicon, silicon carbide, silicon nitride, silicon oxide, silicon oxynitride, titanium oxide, niobium oxide, aluminum oxide, dopants thereof, or any combination thereof, and wherein a difference between the first refractive index and the second refractive index is about +/−0.001 to about +/−0.1; and

removing the second layer deposited on the mask and removing the mask from the first layer, wherein the first group of the grating structures is exposed and the second group of the grating structures contains the second layer deposited thereon.

* * * * *