US 20240003000A1

(19) **United States**

(12) **Patent Application Publication**

ZHU et al.

(10) **Pub. No.: US 2024/0003000 A1**

(43) **Pub. Date: Jan. 4, 2024**

(54) **METHOD AND APPARATUS FOR DEPOSITION OF MENTAL NITRIDES**

(71) Applicant: **Applied Materials, Inc.**, Santa Clara, CA (US)

(72) Inventors: **Mingwei ZHU**, San Jose, CA (US); **Zihao YANG**, Santa Clara, CA (US); **Nag B. PATIBANDLA**, Pleasanton, CA (US); **Ludovic GODET**, Sunnyvale, CA (US); **Yong CAO**, San Jose, CA (US); **Daniel Lee DIEHL**, Chiba (JP); **Zhebo CHEN**, San Jose, CA (US)

(21) Appl. No.: **18/201,055**

(22) Filed: **May 23, 2023**

Related U.S. Application Data

(63) Continuation of application No. 16/823,182, filed on Mar. 18, 2020, now Pat. No. 11,739,418.

(60) Provisional application No. 62/822,585, filed on Mar. 22, 2019.

Publication Classification

(51) **Int. Cl.**

C23C 14/56	(2006.01)
C23C 14/06	(2006.01)
C23C 14/34	(2006.01)
H01J 37/34	(2006.01)

(52) **U.S. Cl.**

CPC ***C23C 14/564*** (2013.01); ***C23C 14/0641*** (2013.01); ***C23C 14/34*** (2013.01); *H01J 2237/24514* (2013.01); ***H01J 37/3441*** (2013.01); ***H01J 37/3405*** (2013.01); ***H01J 37/3464*** (2013.01)

(57) **ABSTRACT**

A structure including a metal nitride layer is formed on a workpiece by pre-conditioning a chamber that includes a metal target by flowing nitrogen gas and an inert gas at a first flow rate ratio into the chamber and igniting a plasma in the chamber before placing the workpiece in the chamber, evacuating the chamber after the preconditioning, placing the workpiece on a workpiece support in the chamber after the preconditioning, and performing physical vapor deposition of a metal nitride layer on the workpiece in the chamber by flowing nitrogen gas and the inert gas at a second flow rate ratio into the chamber and igniting a plasma in the chamber. The second flow rate ratio is less than the first flow rate ratio.




Atomic Percent Nitrogen
Weight Percent Nitrogen
Temperature (°C)
L
L + N2
α - Nb(N)
α - Nb(N) + β - Nb2N
β - Nb2N
β - Nb2N + γ - Nb4N3
γ - Nb4N3
ε + δ
ε - NbN
δ - NbN1-x + N2
~2430 °C
~2200 °C
~2350 °C
1370 °C
20
30
40
50
60
5
10
15
0
500
1000
1500
2000
2500
3000
2460
Nb

FIG. 1


160
166
162
164
166
N2
Ar
Pulsed DC
132
133
Nb target
110
Si Wafer
ESC
High Vacuum Pump
Controller
170
140
10
120a
120
130
184
126
118
152
150
116
182
180
111
112
114
190
100

FIG. 2


N2 Low to High
N2 High to Low
N2 Flow (sccm)
Target Voltage (V)
202
204
206

FIG. 3



FIG. 5



FIG. 6



FIG. 4


300
330
330
100
100
MICRO-
PROCESSOR
CONTROLLER
350
11
325
320
310
325
315
315

FIG. 7


400
132
133
100
130a
130c
422
A
430
420
B
140c
140a
414
116
412
426
410
110
160
10
120a
118
121
120
114
150
137
136

FIG. 8



FIG. 9

METHOD AND APPARATUS FOR DEPOSITION OF MENTAL NITRIDES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation of U.S. application Ser. No. 16/823,182, filed Mar. 18, 2020, which claims priority to U.S. Provisional Application Ser. No. 62/822,585, filed on Mar. 22, 2019, the disclosure of which is incorporated by reference.

BACKGROUND

Technical Field

[0002] The disclosure concerns a reactor for processing a workpiece to deposit a metal nitride, particularly a metal nitride that is suitable as a superconductive material.

Background Discussion

[0003] In the context of superconductivity, the critical temperature (T_C) refers to the temperature below which a material becomes superconductive. Niobium nitride (NbN) is a material that can be used for superconducting applications, e.g., superconducting nanowire single photon detectors (SNSPD) for use in quantum information processing, defect analysis in CMOS, LIDAR, etc. The critical temperature of niobium nitride depends on the crystalline structure and atomic ratio of the material. For example, referring to FIG. **1**, cubic δ-phase NbN has some advantages due to its relatively "high" critical temperature, e.g., 9.7-16.5° K.

[0004] Niobium nitride can be deposited on a workpiece by physical vapor deposition (PVD). For example, a sputtering operation can be performed using a niobium target in the presence of nitrogen gas. The sputtering can be performed by inducing a plasma in the reactor chamber that contains the target and the workpiece.

SUMMARY

[0005] In one aspect, a method of forming a structure including a metal nitride layer on a workpiece includes pre-conditioning the chamber by flowing nitrogen gas and an inert gas at a first flow rate ratio into the chamber and igniting a plasma in the chamber before placing the workpiece in a chamber that includes a metal target, evacuating the chamber after the preconditioning, placing the workpiece on a workpiece support in the chamber after the preconditioning, and performing physical vapor deposition of a metal nitride layer on the workpiece in the chamber by flowing nitrogen gas and the inert gas at a second flow rate ratio into the chamber and igniting a plasma in the chamber. The second flow rate ratio is less than the first flow rate ratio.

[0006] In another aspect, a physical vapor deposition system includes chamber walls forming a chamber, a support to hold a workpiece in the chamber, a vacuum pump to evacuate the chamber, a gas supply to deliver nitrogen gas and an inert gas to the chamber, an electrode to support a metal target, a power source to apply power to the electrode, and a controller. The controller is configured to, cause the gas source flow nitrogen gas and the inert gas at a first flow rate ratio into the chamber and cause the power source to apply power sufficient to ignite a plasma in the chamber to pre-conditioning a chamber before a workpiece on which a metal nitride layer is to be deposited is placed in the chamber, and to cause the gas source flow nitrogen gas and the inert gas at a second flow rate ratio into the chamber and cause the power source to apply power sufficient to ignite a plasma in the chamber to deposit a metal nitride layer on the workpiece by physical vapor deposition after the workpiece is placed in the chamber. The second flow rate ratio is less than the first flow rate ratio.

[0007] In another aspect, a cluster tool for fabrication of a device having a metal nitride layer includes a load lock chamber to receive a cassette holding workpieces, a central vacuum chamber, a plurality of deposition chambers arranged in a cluster formation around and coupled to the central vacuum chamber, a robot to carry a workpiece between the vacuum chamber and the load lock chamber and plurality of deposition chambers, and a controller. The plurality of deposition chambers including a first deposition chamber having a first target, a second deposition chamber having a second target, and a third deposition chamber having a third target. The controller is configured to cause the robot to carry the substrate to the first deposition chamber and to cause the first deposition chamber to deposit a buffer layer on the workpiece, to cause the robot to carry the substrate from the first deposition chamber to the second deposition chamber and to cause the second deposition chamber to deposit a metal nitride layer suitable for use as a superconductor at temperatures above 8° K on the buffer layer, and to cause the robot to carry the substrate from the second deposition chamber to the third deposition chamber and to cause the third deposition chamber to deposit a capping layer on the metal nitride layer.

[0008] In another aspect, a physical vapor deposition system includes chamber walls forming a chamber, a first target support to hold a first target, a second target support to hold a second target, and a third target support to hold a third target, a movable shield positioned in the chamber and having an opening therethrough, an actuator to move the shield, a workpiece support to hold a workpiece in a lower portion of the chamber, a vacuum pump to evacuate the chamber, a gas supply to deliver nitrogen gas and an inert gas to the chamber, a power source to selectively apply power to the first target, the second target or the third target, and a controller. The controller is configured to cause the actuator to move the shield to position the opening adjacent the first target, cause the gas source to flow a first gas into the chamber, and cause the power source to apply power sufficient to ignite a plasma in the chamber to cause deposition of a buffer layer of a first material on the workpiece on the workpiece support, cause the actuator to move the shield to position the opening adjacent the second target, cause the gas source to flow a second gas into the chamber, and cause the power source to apply power sufficient to ignite a plasma in the chamber to cause deposition of a device layer of a second material that is a metal nitride suitable for use as a superconductor at temperatures above 8° K on the buffer layer, the first material being different composition from the second material, cause the actuator to move the shield to position the opening adjacent the third target, cause the gas source to flow a third gas into the chamber, and cause the power source to apply power sufficient to ignite a plasma in the chamber to cause deposition of a capping layer of a third material on the device layer, the third material being different composition from the first and second materials.

[0009] These aspects can include one or more of the following features.

[0010] The metal target may include niobium or a niobium alloy. The metal nitride layer may include niobium nitride or a niobium alloy nitride. The metal target may be substantially pure niobium, and the metal nitride layer may be substantially pure niobium nitride. The metal nitride layer may be δ-phase NbN. The plasma may sputter the metal of the metal target.

[0011] The second flow rate ratio may be 2-30% less than the first flow rate ratio. The first flow rate ratio may be 4:100 to 1:1, and the second flow rate ratio may be 3:100 to 48:52. The chamber may be evacuated to a pressure lower than 10^{-8} Torr.

[0012] Pre-conditioning may include placing a shutter disk on the substrate support. A robot configured to position a shutter disk into the chamber for the pre-condition of the chamber. Pre-conditioning may include heating the shutter disk to a temperature, and performing the physical vapor deposition may include heating the workpiece to the same temperature. The temperature may be 200-500° C. Igniting plasma in preconditioning and igniting plasma in deposition may use the same power level.

[0013] A nitrogen ion concentration in the plasma may be measured with an optical sensor. A flow rate of the nitrogen gas and/or the inert gas may be adjusted in response to nitrogen ion concentration measured by the sensor to bring the nitrogen ion concentration to a desired concentration. The sensor is positioned outside the chamber, and wherein the chamber walls include a window to provide optical access to the chamber for the sensor.

[0014] A sputter shield may be positioning in the chamber. The sputter shield may have an opening to provide a clear line of sight for the sensor to the plasma.

[0015] A buffer layer may be formed on the workpiece before forming the metal nitride layer. The metal nitride layer may be deposited directly on the buffer layer. The buffer layer may be a metal nitride of a metal different than the metal of the target. The buffer layer may be aluminum nitride.

[0016] A capping layer may be formed on the metal nitride layer. The capping layer may include carbon, silicon, a metal different than the metal of the target, or a nitride of a material different than the metal of the target. The capping layer may be carbon, silicon nitride or titanium nitride.

[0017] The first target may be a metal other than a metal of the second target. The first gas may include nitrogen gas. The second target may include niobium. The second gas may include nitrogen gas. The third target may include carbon, silicon, or a metal other than a metal of the second target.

[0018] The shield may be rotatable and the actuator may be configured to rotate the shield.

[0019] Some implementations may provide one or more of the following advantages. The process permits reliable or stable deposition of high quality NbN with a high critical temperature. This permits fabrication of devices, e.g., SNSPD, that operate at higher temperatures, thus making such devices more practical. Devices can be fabricated with higher quantum efficiency and low dark current. Devices can also be fabricated with reduced timing jitter and faster detection response. A buffer layer, a superconductive film, and a capping layer can be deposited by a single tool without removing the workpiece from vacuum. This can significantly improve process stability and manufacturability, and reduces risk of contamination, e.g., oxidation, which also helps preserve the high critical temperature.

[0020] The details of one or more implementations are set forth in the accompanying drawings and the description below. Other potential features, aspects, and advantages will become apparent from the description, the drawings, and the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0021] FIG. **1** is diagram illustrating phase of niobium nitride as a function of processing temperature and atomic percentage nitrogen.

[0022] FIG. **2** is a schematic cross-sectional side view of a reactor to deposit metal nitrides.

[0023] FIG. **3** is a graph illustrating voltage on the target as a function of nitrogen flow and critical temperatures measured for various nitrogen flow values.

[0024] FIG. **4** is a flow chart of a process for depositing a metal nitride.

[0025] FIG. **5** is a schematic cross-sectional view of a device that includes a metal nitride layer for use as a superconductive material during operation.

[0026] FIG. **6** is a flow chart of a process for fabricating a device that includes a metal nitride layer for use as a superconductive material.

[0027] FIG. **7** is a schematic top view of a cluster tool to deposit a seed layer, a metal nitride, and a capping layer.

[0028] FIG. **8** is a schematic side view of a processing chamber to deposit multiple layers of different composition.

[0029] FIG. **9** is a schematic top view of the processing chamber of FIG. **8**.

[0030] Like reference numbers and designations in the various drawings indicate like elements.

DETAILED DESCRIPTION

[0031] As noted above, niobium nitride, particularly δ-phase NbN, has some advantages as a superconductive material. However, δ-phase NbN can be difficult to deposit at a satisfactory quality. For example, it may need a high vacuum (10^{-9} Torr or lower), as well as high mobility species (high temp, high peak power, and low duty cycle in pulsed DC). Although semiconductor grade deposition tools can provide good uniformity, they typically are configured for a lowest vacuum of about 10^{-8} Torr. However, increased pump capacity and additional traps for smaller atomic weight gases, e.g., water vapor, can improve vacuum performance.

[0032] Another issue is that a buffer layer, e.g., an aluminum nitride (AlN) layer, below the (super)conductive layer can help improve the critical temperature of the metal nitride layer. Similarly, a capping layer, e.g., a carbon layer or silicon nitride layer, above the (super)conductive layer can help protect the metal nitride layer, e.g., to prevent oxidation. The capping and buffer layer would typically be provided by separate deposition tools. Unfortunately, removing the workpiece from the tool used for deposition of the metal nitride can result in contamination or oxidation, thus reducing the critical temperature. However, a cluster tool can be configured to have multiple chambers, each of which can deposit a layer without removing the workpiece from the vacuum environment, or a single chamber can be configured to deposit each of the layers, thereby avoiding the need to remove the workpiece.

[0033] Yet another issue is that even under good deposition conditions, reliably depositing a film with as high a critical temperature as possible can be difficult. However, it has been discovered that the critical temperature of niobium nitride as a function of nitrogen content exhibits a hysteresis effect; different critical temperatures can be obtained depending on whether the nitrogen content has been ramped up or ramped down. By performing a preconditioning of the chamber using nitrogen gas before depositing the layer on the workpiece, the process can follow the more advantageous curve of this hysteresis effect. As a result, a higher critical temperature can be obtained more reliably.

Deposition System

[0034] Referring now to FIGS. **2**, a physical vapor deposition (PVD) reactor **100** includes a vacuum chamber **110**. The chamber **110** is enclosed by chamber walls, including a side wall **112**, a floor **114** and a ceiling **116**. A workpiece support **120**, e.g., a pedestal or susceptor, can be positioned inside the chamber **110**. The workpiece support **120** has a top surface **120***a* to support a workpiece **10** inside the chamber **110**. The support **120** can be elevated above the floor **114**.

[0035] In some implementations, a temperature control system can control the temperature of the support **120**. For example, the temperature control system can include a resistive heater embedded in or placed on the surface **120***a* of the workpiece support **120** and a power source electrically coupled to the heater. Alternatively or in addition, coolant channels can be formed in the workpiece support **120**, and coolant from a coolant supply can flow, e.g., be pumped, through the channels.

[0036] In some implementations, the vertical position of the workpiece support **120** is adjustable, e.g., by a vertical actuator.

[0037] An opening **118** (e.g., a slit valve) can be formed in a wall of the chamber **110**. An end effector (not shown) can extend through the opening **118** to place the substrate **10** onto lift pins (not shown) for lowering the substrate onto a support surface **120***a* of the workpiece support **120**.

[0038] In some implementations, the support **120**, or a conductive electrode **121** (see FIG. **8**) within the support, is grounded. Alternatively, an external power source **136** (see FIG. **8**), e.g., a DC or RF power source, can be used to apply a bias voltage or RF power to the support **120** or a conductive electrode **121** within the support **120**, and thus apply a bias voltage or RF power to the workpiece **10**. Optionally, the power source **136** can be coupled to the electrode **121** by an RF matching network **137** (see FIG. **8**).

[0039] A sputter shield **126** can be positioned inside the chamber **110** to prevent sputtering of material onto the chamber side walls **112**.

[0040] An electrode **130** forms a portion of the ceiling **116**, and a target **140** can be supported from the electrode **130**. The electrode **130** is electrically coupled to a power source **132**. The power source **132** can be configured to apply a pulsed DC voltage. The power source **132** can be coupled to the electrode **10** by an RF matching network **133**. The power applied can be 500 W to 20 kW, the voltage can be 200V to 600V, the frequency can be 50 kHz to 250 kHz, and the duty cycle can be 60-100%.

[0041] The target **140** is a body, e.g., a disk, formed of the metal from which the metal nitride is to be deposited. On installation, the target can be substantially pure metal, e.g., a body of substantially pure niobium. However, during processing nitrogen can react with the surface of the target, forming a surface layer of metal nitride.

[0042] A vacuum pump **150** is coupled to the chamber **110**, e.g., by a passage with an opening in a region below the workpiece support **120**, e.g., in the floor **112**, to evacuate the chamber **110**. Examples of vacuum pumps include an exhaust pump with throttle valve or isolation valve, cryogenic pump and turbo pump backed up by a mechanical pump. Although FIG. **2** illustrates a single vacuum pump, in some implementations multiple pumps can be used to increase the vacuum level. The assembly of one or more vacuum pumps **150** can bring the chamber down to a vacuum of less than 8×10^{-9} Torr. The vacuum pumps **150** can maintain a rate of rise of less than 50 nTorr/min at the elevated deposition temperature.

[0043] A condensation plate **152** can be located in the passage connecting the chamber **110** to the vacuum pump **150**. The condensation plate **152** provides a surface of or positioned in the passage that is cooled sufficiently for water to condense on the plate **152**. Thus, the condensation plate **152** acts to capture trap water vapor, and other lower-weight molecules that can condense, thus preventing such gas from forming part of the plasma and reducing the impurity in the metal nitride film.

[0044] A gas source **160** is fluidically coupled to the chamber **110**. The gas source **160** includes a source **162** of nitrogen gas (N_2) and a source **164** of an inert gas, e.g., argon or helium. Flow rates of the nitrogen gas and the inert gas, and thus the ratio of flow rates, can be controlled by independently controllable valves **166** and mass flow controllers. Although FIG. **2** illustrates separate passages entering the chamber, the gasses could be mixed before entering the chamber **110**, and more complicated gas distributor apparatus, e.g., a gas distribution plate or showerhead, an array of radial passages through the side wall, etc., could be used to distribute gas into the chamber **110**.

[0045] Application of power at an appropriate frequency and power to the electrode **130** by the power source **132** can ignite a plasma **111** in the chamber **110**. In particular, a pulsed DC bias can be applied through the electrode **130** to the sputtering target **140**, and the workpiece support **120** can be electrically floating. The resultant electric field in the chamber **110** ionizes the sputtering gas to form a sputtering plasma **111** that sputters the target **140**, causing deposition of material on the workpiece **10**. The plasma **111** is typically generated by applying a DC power level between 100 Watts and 20 kWatts, e.g., 1-5 kWatts. The power source **132** can supply DC pulses at a frequency 50 kHz to 250 KHz, e.g., 200 kHz. The duty cycle of the pulses can be 50-100%, e.g., 50-70% or 60-100%.

[0046] In some implementations, a magnet assembly **170** is positioned outside the chamber **110**, e.g., above the ceiling **116**. The magnet assembly **170** can help confine the ions in the plasma and increase ion energy on the substrate **10**.

[0047] A controller **190**, e.g., a programmed general purpose computer having a processor, memory and non-transitory storage media to store a computer program, can be coupled to the various components to control the processing system **100**.

[0048] An optical emission sensor **180** can be used to monitors the plasma concentration and/or to monitor the gas composition during deposition. The sensor **180** can be positioned outside the chamber **110**, but be placed adjacent a window **182** through a wall of chamber, e.g., the side wall

112, to have a view of the plasma **111**. If necessary, an aperture **184** can be formed in the shield **126** to provide the sensor **180** with a clear line of sight to the plasma **111**. The optical emission sensor **180** can measure the nitrogen ion concentration in the plasma **111**. In some implementations, the optical emission sensor **180** can also measure the inert gas ion concentration in the plasma **111**. The optical emission sensor **180** can provide these measurements to the controller **190**.

[0049] The controller **190** can be configured to control the gas source **160** to adjust the flow rate(s) of the nitrogen gas and/or the inert gas in response to the measured ion concentration(s). For example, the controller **190** can operate in a feedback loop to control the gas flow rate(s) to bring the nitrogen ion partial pressure to a desired partial pressure, or to bring the nitrogen ion concentration to a desired concentration. The controller **190** can also be configured to control gas flow rates of the gas source **160** to maintain a stable plasma and/or achieve a desired condition on the surface of the target **140**.

Deposition of Niobium Nitride

[0050] The workpiece processing tool **100** can be employed to perform deposition of niobium nitride, in particular δ-phase NbN, on a workpiece. In one example, the workpiece **110** includes a buffered layer, e.g., aluminum nitride, onto which the niobium nitride is to be deposited.

[0051] FIG. **3** illustrates voltage on the target as a function of nitrogen flow. A fixed pulsed DC power was applied to the target. The potential of the target was measured with respect to the ground. This potential will change depending on the sputtering yield of the target and ion concentration in the plasma. In general, the target voltage can be a stand-in value for the critical temperature, albeit not as a linear relationship.

[0052] In general, a higher quality film will exhibit both a higher critical temperature. As noted above, it has been discovered that the critical temperature of niobium nitride as a function of nitrogen content exhibits a hysteresis effect. Still referring to FIG. **3**, where the nitrogen flow rate is being increased for successive workpieces, the target voltage follows curve **202**. It is believed that the surface of the niobium target goes from a metallic mode to a "poisoned" mode when sufficient N_2 is present in the chamber to form a thin layer of NbN on the target surface. In contrast, where the nitrogen flow rate is being decreased for successive workpieces, the target voltage follows curve **204**. Again, it is believed that as the N_2 partial pressure decreases, the target starts to become "de-poisoned" and switch back to the metallic mode.

[0053] For both curves **202**, **204**, the target voltage has a maximum value just before a sudden drop. It is believed that this is because niobium-rich niobium nitride (NbN) film is typically formed if the target is in the metallic mode, whereas a NbN film with good stoichiometry and desired cubic phase is typically formed if the target is in the poisoned mode.

[0054] However, where the flow rate is being successively decreased (curve **204**), the drop-off of the target voltage occurs at a lower nitrogen flow rate. This may indicate that the partial pressure where the niobium target is de-poisoned, is lower than the partial pressure at which the niobium target becomes poisoned.

[0055] In addition, where the flow rate is being successively decreased, the target voltage actually reaches a higher value (indicated at **206**), as compared to where the flow rate is being successively increased (curve **202**). Moreover, measurement of the critical temperatures of the niobium nitride deposited at these flow rates confirms that a higher critical temperature can be achieved if the nitrogen flow rate has been decreased rather than increased as compared to a prior process.

[0056] It is possible to take advantage of this hysteresis effect. In particular, by performing a preconditioning of the chamber using nitrogen gas before depositing the layer on the workpiece, the process can follow the more advantageous curve of this hysteresis effect. As a result, a higher critical temperature can be obtained more reliably.

[0057] Referring to FIGS. **2** and **4**, a process **260** for fabricating the metal nitride layer begins by preconditioning the chamber **110** (step **262**). The chamber **110** is evacuated. A shutter disk, e.g., a metal disk of about the same diameter but thicker than a workpiece, can be placed on the support **120** (the workpiece on which the layer is to be deposited is not present in the chamber **110**). The gas distribution assembly **160** supplies nitrogen gas to the chamber **110**.

[0058] The gas distribution assembly **160** can also supply an inert gas, e.g., argon or helium, to the chamber **100**. The inert gas can be used to dilute the nitrogen gas; this can increase plasma density. The gas distribution assembly **160** can establish a total pressure (nitrogen and inert gas) of 2 to 20 mTorr. In this preconditioning step, the nitrogen gas is supplied at a first flow rate, e.g., 15 to 40 sccm, e.g., 20 sccm. The nitrogen gas and the inert gas can be supplied at a first ratio, 4:100 to 1:4, e.g., 4:100 to 1:1, e.g., 2:1 to 1:1, of nitrogen to inert gas (the ratio can be a ratio of flow rates in sccm). Power is applied to the electrode **130**, e.g., as described above, to induce the plasma **111**.

[0059] This conditioning process can be carried out with the shutter disk at a temperature of, e.g., 200-500° C. The preconditioning process can proceed, e.g., for 60-300 seconds.

[0060] After preconditioning, the chamber is evacuated again, e.g., drawn down to 10^{-9} Torr, the dummy substrate is removed, and the workpiece is placed into the chamber **110** and onto the support **120**.

[0061] Now the metal nitride can be formed on the workpiece by a physical vapor deposition process (step **264**). The gas distribution assembly **160** supplies nitrogen gas to the chamber **110**, and power is applied to the electrode **130**, e.g., as described above, to induce a plasma **111**. The power source **132** can apply the same RF power, frequency and duty cycle during deposition as in preconditioning.

[0062] In the deposition step, the nitrogen gas is supplied at a second flow rate that is lower than the first flow rate, while the flow rate of the inert gas remains the same as in the preconditioning step. For example, the second flow rate of the nitrogen gas can be at least 2% lower, e.g., at least 10% lower. For example, the second flow rate can be 2-30% lower, e.g., 10-30% lower. For example, the second flow rate can be 15-18 sccm.

[0063] Alternatively, the flow rate of the nitrogen gas could be held constant, but the flow rate of the inert gas could be increased.

[0064] In the deposition step, the nitrogen gas and the inert gas can be supplied at a second ratio, e.g., 3:100 to 1:6, e.g., 3:100 to 45:52, e.g., 1.5:1 to 1:3, of nitrogen to inert gas (the

ratio can be a ratio of flow rates in sccm). The second ratio can be less than the first ratio, e.g., at least 2% lower, e.g., at least 10% lower. For example, the second ratio can be 2-30% lower, e.g., 10-30% lower.

[0065] This physical vapor deposition process can be carried out with the workpiece at a temperature of, e.g., 200-500° C. The workpiece can be processed at the same temperature as the shutter disk in the preconditioning process. The deposition process can proceed, e.g., for 10-600 seconds.

[0066] Application of power to the electrode **130** at appropriate frequency and duty cycle will ignite plasma in the chamber **110**. The plasma will cause sputtering of material from the target **130** onto the workpiece **10**. Due to the presence of nitrogen in the plasma, a combination of nitrogen and the metal, e.g., niobium nitride, is deposited onto the workpiece. The preconditioning process can enable the deposition of NbN of the right stoichiometry and crystal quality from the beginning to end of the deposition process.

[0067] Appropriate processing conditions for the physical vapor deposition to form δ-phase NbN should be about in the ranges discussed above, although differences in process chamber configuration, etc., can cause variations. If necessary, appropriate process conditions can be determined empirically.

[0068] Finally, the chamber **110** is evacuated again and the workpiece is removed.

[0069] Although the discussion above focuses on niobium nitride, these techniques can be applicable for other metal nitrides, e.g., a nitride of a mixture of niobium with another metal, e.g., NbTiN.

Multilayer Device

[0070] FIG. **5** is a schematic illustration of some layers in a device **220** that includes a metal nitride layer **226** for use as a superconductive material. The device **220** could be superconducting nanowire single photon detectors (SNSPD), a superconducting quantum interference device (SQUID), a circuit in a quantum computer, etc. FIG. **6** is a flowchart of a method of fabrication of the layers.

[0071] Initially, a buffer layer **224** can be deposited on a substrate **222** (step **250**). The substrate can be, for example, a silicon wafer. Although illustrated as a single block, the substrate **222** could include multiple underlying layers.

[0072] The buffer layer **224** can be a material to help improve the critical temperature of the metal nitride, especially when the metal nitride layer is thin. Alternatively or in addition, the buffer layer **224** can improve adhesion between the metal nitride layer **226** and the substrate **222**. The buffer layer **224** can be dielectric or conductive but is not superconductive at the operating temperature of the device **200**. In some implementations, the buffer layer **224** is be formed of a different metal nitride than the metal nitride used for layer **226**. For example, the buffer layer **224** can be formed of aluminum nitride (AlN), hafnium nitride (HfN), gallium nitride (GaN), or indium nitride (InN). Alternatively, the buffer layer **224** could be formed of a carbide, e.g., silicon carbide. The buffer layer can have a (002) c-axis crystal orientation. The buffer layer **224** can be deposited by a standard chemical vapor deposition or physical vapor deposition process.

[0073] Next, the metal nitride layer **226** is deposited on the buffer layer (step **260**). The metal nitride layer **226** can be deposited using the two-step process **260** and system **100** discussed above.

[0074] After the metal nitride layer **226** is deposited, a capping layer **228** can be deposited on the metal nitride layer **226** (step **270**). The capping layer **228** serves as a protective layer, e.g., to prevent oxidation of the metal nitride layer **226** or other types of contamination or damage. The capping layer **228** can be dielectric or conductive but is not superconductive at the operating temperature of the device **200**. In some implementations, the capping layer **228** is a nitride of a different material from the metal of the metal nitride used for layer **226**. In some implementations, the capping layer **228** is a metal different from the metal of the metal nitride used for layer **226**. Examples of materials for the capping layer **228** include carbon, silicon, titanium nitride (TiN), and silicon nitride (SiN). The buffer layer **224** can be deposited by a standard chemical vapor deposition or physical vapor deposition process.

[0075] Etching can be used to form trenches **230** through at least the metal nitride layer **226** to form the conductive lines or other structures needed for the device (step **280**). Although FIG. **4** illustrates the trench as extending through the buffer layer **224**, metal nitride layer **226** and capping layer **228**, other configurations are possible. For example, if the buffer layer **224** and capping layer **228** are both dielectric, then the etching can extend through just the metal nitride layer **226**. In this case, the etching step **280** could be performed before the step **270** of depositing the capping layer. As a result, the capping layer **228** could directly contact the buffer layer **224** in regions between the metal nitride islands. For example, if the buffer layer **224** and capping layer **228** are both dielectric, then the etching can extend through just the metal nitride layer **226**. As another example, the etch can extend through the metal nitride layer **226** and the buffer layer **224** or the capping layer **228** (but not both).

Tool For Multilayer Fabrication

[0076] As noted above, removing the workpiece from a tool used for deposition can result in contamination or oxidation, thus reducing the critical temperature.

[0077] One technique to avoid this issue is to use a cluster tool with multiple chambers, each of which can deposit a layer without removing the workpiece from the vacuum environment. FIG. **7** is a schematic top view of a cluster tool **300** to deposit the buffer layer, the metal nitride layer, and the capping layer. The cluster tool **300** includes one or more central vacuum chambers **310**, one or more fab interface units **315** to receive cassettes that hold workpieces, and one or more robots **320** to transfer workpieces from the fab interface units **315** to other processing chambers, between the processing chambers, and from the processing chambers back to the fab interface units **315**.

[0078] The processing chamber of the cluster tool **300** includes one or more physical vapor deposition chambers **325** for deposition of the buffer layer, e.g., for deposition of aluminum nitride (AlN), one or more physical vapor deposition chambers, e.g., a physical vapor deposition chamber **100** as described above, for deposition of the metal nitride layer, and one or more physical vapor deposition chambers **330** for deposition of the capping layer, e.g., for deposition of a carbon layer. Chambers can be separated by appropriate

slit valves. The cluster tool **300** can be controlled by a controller **350**, e.g., a general purpose programmable computer.

[0079] Another technique to avoid the need to remove the workpiece from vacuum is to deposit each of the layers in a single chamber. FIG. **8** is a schematic side view of a physical vapor deposition reactor **400** to deposit multiple layers of different composition. For example, the physical vapor deposition reactor **400** can be used to deposit the buffer layer, the metal nitride layer, and the capping layer. FIG. **9** is a top view of the physical vapor deposition reactor **400** (FIG. **8** can be considered along section line **8-8** in FIG. **9**).

[0080] The physical vapor deposition reactor **400** is constructed in a manner similar to physical vapor deposition reactor **100**, but includes three separate targets **140***a*, **140***b*, **140***c* (additional targets can be present if needed for other layers). The targets can be supported on the ceiling **116** of the chamber **110** of the reactor **400**. Each target is supported on a respective electrode **130***a*-**130***c*. The different electrodes **130***a*-**130***c* can be coupled to a common power source **132**, or to different power sources **132**.

[0081] A rotatable shield **410** is positioned inside the chamber **110** and is shared by all the electrodes **130**. The shield **410** can be suspended from the ceiling **116** by shaft **420**, and the shaft can be rotated (shown by arrow A) about a vertical axis **426** by an actuator **422**. In some implementations, the actuator **422** can also move the shield **410** vertically (shown by arrow B).

[0082] The rotatable shield **410** can have a hole **412** to expose a corresponding target. The shield **410** advantageously limits or eliminates cross-contamination between the plurality of targets **140***a*-**140***c*. The rotatable shield **410** can also have a pocket **414** for each target that is not being sputtered. For example, in some embodiments where three electrodes **130** are provided, the shield **410** can include a hole **412** to expose one target at a time, and two pockets **414** to house the targets that are not being sputtered. By rotating the shield **410**, a different target can be exposed and operated.

[0083] In some embodiments, the physical vapor deposition reactor **400** includes a plurality of grounding rings **430** to provide improved grounding of the shield **116** to the ceiling **116**, e.g., when the shield **410** is in the retracted position.

[0084] The three targets **140***a*, **140***b*, **140***c* are formed of different materials, e.g., the materials to be sputtered to form the buffer layer, metal nitride layer and capping layer, respectively. For example, a first target **140***a* can be composed of the non-nitrogen component, e.g., the metal, of the element or compound used for the buffer layer. For example, if the buffer layer is to be formed of aluminum nitride, the first target **140***a* can be aluminum. The second target **140***b* can be the non-nitrogen component, e.g., the metal, of the compound used for the superconductive layer. For example, if the superconducting layer is to be formed of niobium nitride, the second target **140***a* can be niobium. The third target **140***c* can be the non-nitrogen component of the element or compound used in the capping layer, e.g., carbon, silicon or titanium.

[0085] In operation, the actuator **422** rotates the shield **410** so that the aperture **412** is aligned with the first target **140***a* and the other targets are covered. The vacuum pump **150** evacuates the chamber **110**, the gas source **160** supplies a sputtering gas to the chamber **110**, and the power source **132** applies a power to the electrode **130***a* to generate a plasma in the chamber. The plasma can cause sputtering of the material of the first target **140***a*, resulting in physical vapor deposition of the buffer layer onto the substrate **10**. If appropriate, the gas source can supply nitrogen or another gas that will form a compound with the material of the first target **140***a*. For example, if aluminum nitride is to be deposited, the first target **140***a* can be aluminum and the gas source can supply both an inert gas, e.g., argon, and nitrogen. If the material of the first target **140***a* is to be deposited as a substantially pure element, then the gas can include only inert elements, e.g., argon or xenon.

[0086] When deposition of the buffer layer is complete, the chamber **110** is evacuated, and the actuator **422** rotates the shield **410** so that the opening **412** is aligned with the second target **140***b* and the other two targets are covered. The material of the metal nitride layer, e.g., niobium nitride, can be deposited according to the method described above.

[0087] When deposition of the metal nitride layer is complete, the chamber **110** is evacuated, and the actuator **422** rotates the shield **410** so that the opening **412** is aligned with the third target **140***c*. The material of the capping layer can be deposited, in a manner similar to described above for the buffer layer. The chamber **110** can evacuated again, and the workpiece removed, e.g., by a robot.

Controller

[0088] A controller, e.g., the controller **190** and/or controller **150**, can be implemented in digital electronic circuitry, or in computer software, firmware, or hardware, or in combinations thereof. The controller can include one or more processors, e.g., a controller can be a distributed system. One or more computer program products, i.e., one or more computer programs tangibly embodied in a machine-readable storage media, can be executed by, or control the operation of, the controller, e.g., a programmable processor, a computer, or multiple processors or computers. A computer program (also known as a program, software, software application, or code) can be written in any form of programming language, including compiled or interpreted languages, and it can be deployed in any form, including as a stand-alone program or as a module, component, subroutine, or other unit suitable for use in a computing environment. A computer program does not necessarily correspond to a file. A program can be stored in a portion of a file that holds other programs or data, in a single file dedicated to the program in question, or in multiple coordinated files (e.g., files that store one or more modules, sub-programs, or portions of code). A computer program can be deployed to be executed on one computer or on multiple computers at one site or distributed across multiple sites and interconnected by a communication network.

[0089] The operations of the controller described in this specification can be performed by one or more programmable processors executing one or more computer programs to perform functions by operating on input data and generating output. The operations of the controller can also be performed by, and apparatus can also be implemented as, special purpose logic circuitry, e.g., an FPGA (field programmable gate array) or an ASIC (application-specific integrated circuit).

[0090] While particular implementations have been described, other and further implementations may be devised without departing from the basic scope of this

disclosure. It is contemplated that elements and features of one embodiment may be beneficially incorporated in other embodiments without further recitation. It is to be noted, however, that the drawings illustrate only exemplary embodiments. The scope of the invention is determined by the claims that follow.

What is claimed is:

1. A method of forming a structure including a metal nitride layer on a workpiece, comprising:

before placing the workpiece in a chamber that includes a niobium target, pre-conditioning the chamber by flowing nitrogen gas and an inert gas at a first flow rate ratio into the chamber and igniting a plasma in the chamber while the nitrogen gas and the inert gas are flowing at the first flow rate ratio;

after the preconditioning, evacuating the chamber;

after the preconditioning, placing the workpiece on a workpiece support in the chamber; and

performing physical vapor deposition of a niobium nitride or niobium alloy nitride layer on the workpiece in the chamber by flowing nitrogen gas and the inert gas at a second flow rate ratio of nitrogen gas to inert gas into the chamber and igniting a second plasma in the chamber while the nitrogen gas and the inert gas are flowing at the second flow rate ratio, wherein the second flow rate ratio is less than the first flow rate ratio.

2. The method of claim **1**, wherein the metal target comprises substantially pure niobium and the metal nitride layer comprises substantially pure niobium nitride.

3. The method of claim **1**, wherein the second flow rate ratio is 2-30% less than the first flow rate ratio.

4. The method of claim **1**, wherein the first flow rate ratio is 4:100 to 1:1, and the second flow rate ratio is 3:100 to 48:52.

5. The method of claim **1**, wherein pre-conditioning the chamber comprises placing a shutter disk on the substrate support.

6. The method of claim **5**, wherein pre-conditioning comprises heating the shutter disk to a temperature and performing a physical vapor deposition comprises heating the workpiece to the same temperature.

7. The method of claim **6**, wherein the temperature is 200-500° C.

8. The method of claim **6**, wherein igniting plasma in preconditioning and igniting plasma in deposition use a same power level.

9. A physical vapor deposition system, comprising:

chamber walls forming a chamber;

a support to hold a workpiece in the chamber;

a vacuum pump to evacuate the chamber;

a gas supply to deliver nitrogen gas and an inert gas to the chamber;

an electrode to support a metal target;

a power source to apply power to the electrode; and

a controller configured to

before a workpiece on which a metal nitride layer is to be deposited is placed in the chamber, cause the gas source to flow nitrogen gas and the inert gas at a first flow rate ratio of nitrogen gas to inert gas into the chamber and cause the power source to apply power sufficient to ignite a first plasma in the chamber to pre-condition the chamber while the nitrogen gas and the inert gas are flowing at the first flow rate ratio,

after the workpiece is placed in the chamber, cause the gas source to flow nitrogen gas and the inert gas at a second flow rate ratio of nitrogen gas to inert gas into the chamber, wherein the second flow rate ratio is less than the first flow rate ratio and comprises less nitrogen gas than the first flow rate ratio, and

cause the power source to apply power sufficient to ignite a second plasma in the chamber while the nitrogen gas and the inert gas are flowing into the chamber at the second flow rate ratio to deposit the metal nitride layer.

10. The system of claim **9**, comprising the metal target, and wherein the metal target comprises niobium.

11. The system of claim **10**, wherein the metal target is substantially pure niobium.

12. The system of claim **9**, wherein the second flow rate ratio is 2 to 30% less than the first flow rate ratio.

13. The system of claim **12**, wherein the first flow rate ratio is 4:100 to 1:1, and the second flow rate ratio is 3:100 to 48:52.

14. The system of claim **9**, comprising a robot configured to position a shutter disk into the chamber for the pre-condition of the chamber.

* * * * *